











Product description		Application	
Description	Ready-to-use stain with distinct positive character on coniferous wood. Colour metrics stored so that a vast number of colour shades can be mixed. Can also be applied on many type of hardwood. Wax Stain WB contains natural waxes.		 
		Spray pressure (bar)	1,0 - 1,5
		Nozzle size (mm)	0.8-1.3
		Coverage (m ² /l)	4-7 7-9
		Application quantity and yield strongly depend on the type of wood and the way of sanding the wood.	-
Range of application		Drying time @ 20°C	
Description	Almost all types of wood in the interior. Especially on coniferous wood such as spruce, pine, etc. in the interior. Also on softwood with brushed surface for rustic appearance. It is also possible to achieve equalising, excellent colouring on hardwood such as oak or ash without any positive character. The product is only suitable for slightly strained surfaces such as wall and ceiling panellings, room dividers, etc.	Can be further treated	at least 12 hours
Product data		Aftertreatment	
Product code	WB-COLOUR	Brush with the Zweihorn smoothing brush No. 4 in the direction of the wood structure until a silky effect is achieved. The product must not be overpainted with varnish. For better protection of the stain, the surface can be retreated with Zweihorn Naturtrend waxes.	
Product color	as requested	Special notes	
Packaging size	5l 0.75 l	The product is frost-sensitive. Do not store and transport under 5° C.	
Viscosity at delivery DIN 4 mm (sec.)	12 sec. ± 2	Stained surfaces must always be given a follow-up treatment.	
Shelf life - Original container unopened	at least 1 year	After sanding, greasy wood rich in ingredients, such as teak, should first be degreased with Zweihorn® Universal Cleanser UR and a lint-free cloth in the direction of the wood grain.	
Preparation of substrates		The colour depends on the type of wood, on the way of sanding, on the applied quantity of stain and on the subsequent surface treatment. Always make a staining and varnishing test.	
	Graduated sanding of wood Carefully remove the sanding dust. Coarse-pore wood must be brushed out.	If several batches should be used for one object, first mix all of them in a large plastic container in order to avoid colour variations.	
	Optionally wet with water. Sand or smoothen after drying overnight.	The product is not suitable for application on floors or stairs. Slip hazard! For these purposes, please use the care products from our range of parquet products.	
			
Processing			
	Shake or stir well before use!		
			
	Apply the product with spatula, brush or lint-free cloth and carefully remove any excess. The product must first be thoroughly worked into the wood pore crosswise and then lengthwise in the direction of the wood grain.		

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2022-07-05 / 6