

Unocryl One-Pack Waterborne Parquet Primer UC-PG



Product description		Hardener - Thinner - Additives	
Description	Water-thinnable one-pack parquet primer for the preparation of the parquet floor for further coating with Unocryl One-Pack Parquet Primer UC-PG, floors can be primed and prepared for further coating with Unocryl One-Pack Parquet Varnish UC-P or Duocryl 8 Parquet Varnish DC-P. The product reduces the lateral glueing of the parquet floor and is therefore strongly recommended for priming.	Dilution	not required if necessary tap water
Range of application		Application	
Description	The product is suitable for all usual types of wood parquet and cork.		
		Processing viscosity DIN 4mm (sec.)	20
		Coverage per application (g/m ²)	70-125
		Coverage (m ² /l)	8-15
Product data		Drying time @ 20°C	
Product code	UC-PG	Dust dry	at least 40 minutes
Packaging size	1 l 5l	Touch dry	at least 90 min.
Viscosity at delivery DIN 4 mm (sec.)	20 ± 2	Sandable	at least 4 hours
VOC Directive EC limit value for this product (cat. A/i): 140 g/l (2010)	This product contains max. 90 g/l VOC.	Aftertreatment	
Shelf life - Original container unopened	at least 1 year	After sufficient drying, sand with a disk sander and P 150 sanding disks. Then two coats of Unocryl One-Pack Waterborne Parquet Varnish UC-P 8, 9 or Duocryl Two-Pack PUR Waterborne Parquet Varnish DC-P 8, 9 must be applied.	
Preparation of substrates		Test standards	
Depending on the type of wood and the way of installation, graduated sanding must be carried out with raw wooden floors.	P80 to max. P120		General appraisal certificate with regard to low flammability according to DIN 4102/B1 on hardly inflammable B1-tested wooden particle boards, even veneered.
Exotic wood / woods rich in extractives	Insulate before with Duocryl Two-Pack Waterborne PUR Filling and Insulating Primer DC-FI.		
Processing			
Stir thoroughly!			
Mix and apply the product as described under "Hardener Thinner Additives". Use a special application roller for parquet. Pour the product into a paint tray; never pour it directly onto the floor.			

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2021-07-13 / 8