

QUANTUM COLOR P330

sikkens

WOOD COATINGS

INTERIOR

TECHNOLOGY

PU Acrylic

PRODUCT TYPE

Primer

PRODUCT DESCRIPTION

Multifunctional solventborne 2K PU acrylic primer for a high gloss finish. Its good filling power produces a non-yellowing smooth surface with a high impact resistance.

- good filling power
- smooth surface suitable for high gloss
- lightfast
- high impact resistance
- good isolating properties



COLOUR

White

PACK SIZES

QCP330-2 - 5 KG
QCP330-1 - 20 KG

SHELF LIFE

24 months

STORAGE CONDITIONS

Keep cans tightly sealed, in a well ventilated place, with controlled temperature between 10 and 30°C

SOLID CONTENT

55,2% ± 1%

DENSITY (SPECIFIC WEIGHT)

1,35 +/- 1%

DELIVER VISCOSITY

65 sec. ± 2 DIN 6mm

PREPARATION OF SUBSTRATES



Raw wooden surfaces.

P120, P150, P180

HARDENER

Hardener	Ratio (by weight)	Pot Life
HPU6300	10%	Up to 8h

THINNING

TPU 9300-F, Fast drying
TPU 9301-S, Slow drying

APPLICATION METHOD

Spray application airmix/airless, spray application high/low pressure

APPLICATION

Spray pressure (bar)	1.5 - 3.0	110 - 130
Nozzle size (mm)	2.0 - 2.5	0.33 - 0.38
Thinner to be added (%)	0-20	0 - 10
Processing viscosity DIN 4mm (sec.)	30-40	40 - 70
Layer Thickness (g/m ²)	120 - 200	120 - 200

DRYING TIME @ 20°C

Dust dry	At least 20 minutes
Sandable	At least 4 hours

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-03-06 / 20

QUANTUM COLOR P330

sikkens

WOOD COATINGS

INTERIOR

TEST STANDARDS



Tox Control - The label for low-emission furniture coatings

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-03-06 / 20