

TECHNOLOGIA

Wodnorozcieńczalny

RODZAJ PRODUKTU

Podkład wypełniający

OPIS PRODUKTU

Szybkoschnąca jednoskładnikowa wodnorozcieńczalna szpachlówka do spoin parkietowych do mieszania z pyłem szlifierskim.

- Musi być wymieszana z pyłem szlifierskim (ostatnie szlifowanie międzyoperacyjne)
- Szybkoschnąca
- Łatwa w użyciu
- Zamyka szczeliny i otwory oraz redukuje sklejanie boczne

**KOLOR**

Bezbarwny

1 L

OKRES PRZECHOWYWANIA

12 miesięcy

WARUNKI PRZECHOWYWANIA

Trzymać puszki szczelnie zamknięte, w dobrze wentylowanym pomieszczeniu z kontrolą temperatury pomiędzy 10 a 30°C

ZAWARTOŚĆ CIAŁ STAŁYCH

34.4% ± 1%

GĘSTOŚĆ (CIĘŻAR WŁĄŚCIWY)

1,05 +/- 1%

PRZYGOTOWANIE SUBSTRATÓW

Nowe, niemalowane podłogi: w zależności od rodzaju drewna i sposobu układania, należy przeprowadzić podstawowe szlifowanie. Dokładnie usunąć pył za pomocą odkurzacza.	P80 do maks. P120.
Renowacja lakierowanych podłóg: najpierw zeszlifować kompletnie stary lakier. Dokładnie usunąć pył za pomocą odkurzacza	P80 do maks. P120.

METODA APLIKACJI

Szpachelka

OGÓLNA INSTRUKCJA

Po szlifowaniu zbierz powstały pył drzewny do czystego pojemnika. Zmieszaj Aqualit A-PJF100 i mączkę drzewną w proporcjach od 2:1 do 5:1 (w zależności od rodzaju drewna) aby stworzyć miksturę nadającą się do nanoszenia szpachelką. Aqualit A-PJF 100 może być użyty jako rozcieńczalnik. Użyj szpachelki ze stali nierdzewnej aby nałożyć równą ilość na podłogę i wypełnić małe pęknięcia i przerwy. Nakładaj produkt równo i nie zostawiaj nadmiaru na podłodze. Jeśli pęknięcia i przerwy odstonią się ponownie, można jeszcze raz nałożyć miksturę za pomocą szpachelki.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1