DURACID COLOR T440



INTERIOR

TÉCNOLOGIA

Curado ácido

TIPO DE PRODUCTO

Acabado

DESCRIPCIÓN DEL PRODUCTO

Capa de acabado 2K de secado rápido y base disolvente con un largo tiempo de empleo útil y una alta resistencia química.

secado rápido

amarillamiento moderado



COLOR

Base Neutra BN00/Base Blanca BW01

4.6 KG 5 KG 18.4 KG 20 KG

VIDA ÚTIL

12 meses en el envase original sin abrir

CONDICIONES DE ALMACENAJE

Entre 15 y 25°C en condiciones limpias y secas.

CONTENIDO SOLIDO

BW01: aprox. 61 % en peso BN00: aprox. 57 % en peso

DENSIDAD (PESO ESPECÍFICO)

BW01: Aprox. 1,27 kg/l BN00: Aprox. 1,11 kg/l

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably trough trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1

Akzo Nobel Hilden GmbH, Düsseldorfer Str. 96 - 100, 40721 Hilden, Germany. www.sikkens-wood-coatings.com

VISSCOSIDAD DE ENTREGA

Aprox. 140-150 seg DIN Copa 4 @ 23 °C

TEMPERATURA DE APLICACIÓN

Entre 20-25 $^{\circ}\mathrm{C}$ para sustrato, aire y material a aprox. 55 % H.R.

ENDURECEDOR (EN PESO)

н	AC6401 10:1 en volumen	Aprox. 24 Horas
		Aprox. 24 Horus

DILUIR

TAC9400-M; TAC9403-F

MÉTODO DE APLICACIÓN

aplicación a pistola alta/baja presión, cortina

APLICACIÓN

		1-B 1-B
Viscosidad de aplicación DIN 4 mm (seg.)	25-30 seg DIN copa @ 23°C	25-40 seg DIN copa 4 @ 23 °C
Grosor de la Capa (g/m²)	110	110

