

<b>Type of Product</b> 2-pack Pigmented Polyurethane Top Coat	<b>Storage Conditions</b> Between 15 and 25 °C under clean and dry conditions.												
<b>Area of Use</b> Exterior Joinery / Interior Joinery	<b>Methods</b> Spraying												
<b>Additional Information</b> The product contains no aromatic solvents. The product is thixotropic with good sag resistance, which also makes it suitable for application on edges and profiles.	<b>Application Conditions</b> Between 20-25 °C for substrate, air and material at approx. 55 % R.H.												
<b>Packaging</b> 2675-753551-200 - 20 L	<b>Mixing Ratio</b> Coating : Hardener : Thinner 10,0:3,5:0-3,0 by volume												
<b>Suitable Primer</b> US-Grund, D-Dur Primer	<b>Application Viscosity</b> 20-40 sec DIN cup 4 @ 23 °C depending on application equipment. Amount- and choice of thinner depend of application- and line conditions.												
<b>Notes</b> D-DUR 35 reacts chemically with D-Dur Hardener and builds a polyurethane. As primer on windows, US-Grund is recommended.	<b>Applied Amount</b> Approx. 120 µm wet film												
<b>Binder</b> Alkyd	<b>Potlife</b> Approx. 4 Hours @ 20 °C												
<b>Solid Contents</b> Approx. 59 % by weight incl. hardener	<b>Cleaning</b> 6500-008001												
<b>Delivery Viscosity</b> Thixotropic	<b>Empty Packaging</b> Disposal according to local regulations.												
<b>Density</b> Approx. 1,32 kg/l	<b>Remarks</b> Can be applied with different kinds of spraying equipment, even electrostatically, <b>warm spraying should, however, be avoided.</b>												
<b>Hardener</b> 7000-012009	<b>Thermal Drying</b> <table border="1"> <thead> <tr> <th>Temperature (°C)</th> <th>20</th> <th>40</th> </tr> </thead> <tbody> <tr> <td><b>Time to (hours)</b></td> <td></td> <td></td> </tr> <tr> <td>Sandable</td> <td>4-5</td> <td>2-3</td> </tr> <tr> <td>Stackable.</td> <td>8</td> <td>3-4</td> </tr> </tbody> </table>	Temperature (°C)	20	40	<b>Time to (hours)</b>			Sandable	4-5	2-3	Stackable.	8	3-4
Temperature (°C)	20	40											
<b>Time to (hours)</b>													
Sandable	4-5	2-3											
Stackable.	8	3-4											
<b>Thinner</b> 6500-020001	<b>Additional Drying Information</b> Please contact our Technical Staff for specific data concerning curing conditions on your line.												
<b>Shelf Life</b> 12 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.													

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2021-02-17 / 1

## Gloss

Approx. 45-50 GU @ 60°. The final gloss depends on various conditions, i.e. application method, applied amount, drying conditions, etc.

## HSE Information

See Safety Data Sheet for further information.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2021-02-17 / 1

## EMEA HQ

Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 [www.akzonobel.com/wood](http://www.akzonobel.com/wood)