AkzoNobel

Aqualit A-PT230-20



| Product data | | | | | |
|--|---------------------------------------|------------------------|--|---|--|
| Packaging size | | | 1 5 | | |
| Viscosity at delivery DIN 4 mm (sec.) | | | 20 ± 2 | | |
| Shelf life – Original container unopened | | | at least 1 year | | |
| VOC Directive EC limit value for this product (cat. A/i): 140 g/l (2010) | | | This product contains max. 90 g/l VOC. | | |
| Gloss levels | | | | | |
| Product number | Gloss level | DIN 67530 Angle of 60° | | | |
| A-PT230-20 | semi gloss | 20 ± 2 | | | |
| Preparation of substrates | | | | | |
| Aqualit Parquet Sealer A-PS130 must be applied and sanded in accordance with the Technical Data Sheet. | | | | | |
| Processing | | | | | |
| Stir thoroughly! | | | | | |
| Mix and apply the product as described under "Hardener Thinner Additives". Use a special application roller for parquet. Pour the product into a paint tray; never pour it directly onto the floor. | | | | | |
| Hardener - Thinner - Additives | | | | | |
| Dilution | n not required if necessary tap water | | | | |
| Application | | | | | |
| | | | | | |
| Processing viscosity DIN 4mm (sec.) 20 | | | |) | |

| Drying time @ 20°C | |
|----------------------|---------------------|
| Dust dry | at least 40 minutes |
| Touch dry | at least 90 min. |
| Sandable | at least 4 hours |
| Accessible | at least 12 hours |
| Fitting of furniture | at least 24 hours |
| Laying of carpets | at least 7 days |
| First wet cleaning | at least 1 month |

Special notes

The product is frost-sensitive. Do not store and transport under 5° C

Not suitable for thermally or chemically treated wood!

The application of waterborne stains by brush/roller is not recommended since these stains would be partially dissolved by the waterborne lacquer and spots would develop.

Do not use any rusting tools.

In order to guarantee high wear resistance, a sufficient total film thickness must be ensured.

All processing parameters apply to normal conditions (20 °C, 65% rel. air humidity). Deviations may have a negative effect on the result. During processing, take care that the air is exchanged slowly.

Care instructionApplicable to all surface-treated wooden floors: Do not mop too wet in order to avoid the detrimental effect of moisture to joints or borderings.

| Test standards | | | | |
|----------------|---|--|--|--|
| | DIN 68861/1C Chemical exposure of furniture surfaces | | | |
| A P | Abrasion resistance according to DIN 68861, Part 2 | | | |
| CE | Building products complying with the technical DIBT rules. CE marking can be requested for structures likes parquet, stairs, etc. AgBB approval for the use on parquet and wooden floors according to DIN EN 14342. | | | |
| | 1 | | | |

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably trough trial processing. If in any doubt as to the handling or processing of the purchaser product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of a portice darget and suitability of a product specifications, yet the use thereof lies entirely within the responsibility of application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2020-07-16 / 7

70-125

8-15

EMEA HQ Akzo Nobel Hilden GmbH • Düsseldorfer Str. 96 - 100 • 40721 Hilden • Germany • www.akzonobel.com/wood

AN 204450 060919

Coverage (m²/l)

Coverage per application (g/m²)