

<p><b>Type of Product</b></p> <p>Top Coat Transparent UV Curing</p>	<p><b>Application Conditions</b></p> <p>Between 30-45 °C for substrate, air and material at approx. 55 % R.H.</p>
<p><b>Area of Use</b></p> <p>Interior Joinery / Furniture</p>	<p><b>Application Viscosity</b></p> <p>Ready for use, delivery viscosity</p>
<p><b>Packaging</b></p> <p>4120-056101-206 - 24 KG</p>	<p><b>Applied Amount</b></p> <p>Approx. 4-8 g/m<sup>2</sup> dry film</p>
<p><b>UV Curing Products</b></p> <p>UV lacquers react when exposed to ultra-violet radiation, including sunlight. When using UV-Curing products on absorbing substrates like MDF or porous woods, unreacted material can be retained in the substrate. If the product is used on these substrates, attention should be given to the choice of sealer. Consult our Technical Staff for recommendations relating to your specific line conditions.</p>	<p><b>Cleaning</b></p> <p>6500-008001 or 6800-001001 or 6800-005001</p>
<p><b>Binder</b></p> <p>Acrylate</p>	<p><b>Empty Packaging</b></p> <p>Disposal according to local regulations.</p>
<p><b>Solid Contents</b></p> <p>Approx. 100 % by weight</p>	<p><b>UV Curing</b></p> <p>The curing depends on various conditions, i.e. applied amount, UV intensity, line speed, temperature, etc. Cures by UV radiation only.</p>
<p><b>Delivery Viscosity</b></p> <p>100 - 700 mPasCAP2000 #1/400 @ 35 °C</p>	<p><b>Additional Drying Information</b></p> <p>Please contact our Technical Staff for specific data concerning curing conditions on your line.</p>
<p><b>Density</b></p> <p>1,09 +/- 0,05 kg/l</p>	<p><b>Gloss</b></p> <p>10+/- 3 GU @ 60°. The final gloss depends on various conditions, i.e. application method, applied amount, drying conditions, etc.</p>
<p><b>Shelf Life</b></p> <p>12 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.</p>	<p><b>HSE Information</b></p> <p>Use safety gloves and safety eyewear/face shield during the work. See Safety Data Sheet for further information.</p>
<p><b>Storage Conditions</b></p> <p>Between 15 and 25 °C under clean and dry conditions. Protect from direct sunlight. During Transportation and Storage the material must not be exposed to temperatures below 5°C.</p>	
<p><b>Methods</b></p> <p>Smooth roller coater</p>	

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-03-13 / 14