

| | |
|--|---|
| Type of Product Waterborne Transparent Lacquer | Storage Conditions Between 15 and 25 °C under clean and dry conditions. Protect from direct sunlight. During Transportation and Storage the material must not be exposed to temperatures below 5°C. |
| Area of Use Furniture / Flooring / Interior Joinery | Methods Indirect rotogravure printing system |
| Packaging 3000-001001-206 - 18 KG 3000-001001-200 - 18 L | Application Conditions Between 20-35 °C for substrate, air and material at approx. 55 % R.H. |
| Alternative Product Number 36166 | Application Viscosity 18-25 sec DIN cup 4 @ 23 °C |
| Notes CLEAR INK cannot be used on its own. Should be mixed with Ink Tinter and must always be overcoated with suitable lacquer. Intended for industrial coating in printing lines. Gives pattern on wood related material. | Cleaning Water and/or 8500-069001 (65588) |
| Binder Acrylic | Empty Packaging Disposal according to local regulations. |
| Solid Contents 20 +/- 5 % by weight | Remarks Specially designed for indirect printing rollers. Contact our Technical Staff regarding mixing ratio, application description, etc. Do not sand the applied print. |
| Delivery Viscosity 15-25 sec DIN Cup 4 @ 23 °C | HSE Information See Safety Data Sheet for further information. |
| Density 1,02 +/- 0,05 kg/l | |
| pH value 8-9 | |
| Thinner Water | |
| Shelf Life 18 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability. | |

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-10-03 / 3