

Type of Product Waterborne Transparent Sealer	Cleaning Water
Area of Use Interior Joinery / Exterior Joinery	Empty Packaging Disposal according to local regulations.
Additional Information The wood must be dry and contain max. 15 % moisture.	Remarks 3 Can be recoated with most AN mid-coats and finishes, please consult our Technical staff. Recoatable after app. 1 hour/23°C at 50% RH. This product must have become transparent before overcoating.
Notes For application to exposed end grain of primed or base stained joinery. Quick drying and good adhesion. Must be recoated before being exposed externally.	Additional Drying Information Ensure good ventilation when drying waterborne products. Please contact our Technical Staff for specific data concerning curing conditions on your line.
Binder Acrylic	HSE Information See Safety Data Sheet for further information.
Solid Contents Approx. 29 % by volume	
Delivery Viscosity Thixotropic	
Density Approx. 1,02 kg/l	
Shelf Life 12 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.	
Storage Conditions Keep from freezing. Between 15 and 25 °C under clean and dry conditions.	
Methods Manual application	
Application Conditions Min. 10 °C	
Application Viscosity Ready for use, delivery viscosity	

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2021-02-17 / 1

EMEA HQ
Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood