

TECHNOLOGY

Waterborne

PRODUCT TYPE

Primer

PRODUCT DESCRIPTION

Water-thinnable one-pack parquet primer for the preparation of the parquet floor for further coating with Aqualit PS130, floors can be primed and prepared for further coating with Aqualit PT230-20 or Aqualit PT260-20. The product reduces the lateral glueing of the parquet floor and is therefore strongly recommended for priming. The product is suitable for all usual types of wood parquet and cork.



SHELF LIFE

12 months in original, unopened package

STORAGE CONDITIONS

Between 15 and 25°C under clean and dry conditions.

SOLID CONTENT

28% ± 2%

DENSITY (SPECIFIC WEIGHT)

1,03 +/- 1%

DELIVER VISCOSITY

20 ± 2 Viscosity at delivery DIN 4 mm

VOC (G/L)

VOC Directive EC limit value for this product (cat. A/i): 140 g/l (2010). This product contains max. 90 g/l VOC.

PREPARATION OF SUBSTRATES

	Depending on the type of wood and the way of installation, graduated sanding must be carried out with raw wooden floors.	P80 to max. P120
--	--	------------------

THINNING

not required if necessary tap water

APPLICATION METHOD

Stir thoroughly!
Use a special application roller for parquet. Pour the product into a paint tray; never pour it directly onto the floor.

DRYING TIME @ 20°C

Dust dry	At least 40 minutes
Touch dry	At least 90 minutes
Sandable	At least 4 hours

GENERAL INSTRUCTION

Aftertreatment:
After sufficient drying, sand with a disk sander and P 150 sanding disks. Then two coats of Aqualit PT230-20 or Aqualit PT260-20 must be applied.

TEST STANDARDS

	General appraisal certificate with regard to low flammability according to DIN 4102/B1 on hardily inflammable B1-tested wooden particle boards, even veneered.
--	--

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-02-24 / 10