







Purolit 2K-PUR Top-Klarlack PL-T-8 PL-T-9



Product description		Application		
Description	Two-pack, solvent-thinnable, lightfast, clear PU topcoat	Spray pressure (bar)	1.5-2.0 110-130	
		Nozzle size (mm)	1.6-2.0 0.23-0.28	
		Thinner to be added (%)	0-20 0-20	
		Processing viscosity DIN 4mm (sec.)	25 25	
		Coverage per application (g/m²)	100-120 100-120	
		Coverage (m²/l)	8-10 8-10	
Range of application		Drying time @ 20°C		
Description	Almost all wooden furniture in the interior. Open- or closed-pore coatings. Top coat on Wigranit® Novacolor WNC/colour paint.	Dust dry	at least 20 minutes	
		Touch dry	at least 1 hour	
		Ready for transport	at least 12 hours	
		Sandable	at least 2 hours	
Product data		Aftertreatment		
Product code	PL-T-8 PL-T-9	After sanding with P280-320 grit paper, the surface can be retreated with the same product at any time.		
Packaging size	25l	Test standards		
Viscosity at delivery DIN 4 mm (sec.)	30 ± 2		DIN 68861/1B Chemical exposure of furniture surfaces	
Shelf life – Original container unopened	at least 2 years			
Gloss levels				
Product number	Gloss level	DIN 67530 Angle of 60°		
PL-T-8	semi gloss	30 ± 2		
PL-T-9	semi matt	20 ± 2		
Preparation of substrates				
	Raw wooden surfaces. Graduated sanding of wood Carefully remove the sanding dust Coarse-pore wood must be brushed out.	P120, P150, P180		
Processing				
	Stir thoroughly!			
Hardener - Thinner - Additives				
	Hardening	10% PUR 4084		
	Dilution	S 9029 slow drying S 8003 normal drying		
	Pot life 20°C, 65% rel. humidity	up to 36 hours		

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2025-03-10 / 34