

TECHNOLOGIA

Wodnorozcieńczalny

RODZAJ PRODUKTU

Lakier nawierzchniowy

OPIS PRODUKTU

Światłotrwwały dwuskładnikowy wodnorozcieńczalny lakier parkietowy o ekstremalnej odporności na ścieranie

- Dobra przejrzystość
- Ekstremalna odporność na ścieranie
- Bardzo dobra odporność mechaniczna i chemiczna
- Łatwy w nakładaniu i szlifowaniu
- Szybkoschnący

**KOLOR**

Bezbarwny

POZIOM POŁYSKU (OK.GU @ 60°)

20

5 L

OKRES PRZECHOWYWANIA

12 miesięcy

WARUNKI PRZECHOWYWANIA

Trzymać puszki szczelnie zamknięte, w dobrze wentylowanym pomieszczeniu z kontrolą temperatury pomiędzy 10 a 30°C

ZAWARTOŚĆ CIAŁ STAŁYCH

30% ± 1

GĘSTOŚĆ (CIĘŻAR WŁAŚCIWY)

1,04 +/- 1%

LEPKOŚĆ HANDLOWA

20 ± 2 lepkość handlowa DIN 4 mm (s)

PRZYGOTOWANIE SUBSTRATÓW

Aqualit Parquet Sealer A-PS130 musi być nakładany i szlifowany zgodnie z Kartą Danych Technicznych

P120
-
P150.**UTWARDZACZ (WAGOWO)**

HWA 6000

5%

do 2 godzin

ROZCIEŃCZANIE

woda kranowa

METODA APLIKACJI

Pędzel, wałek

APLIKACJA

Lepkość robocza DIN 4 (s)	20
Grubość warstwy (g/m²)	70 - 125

CZAS SCHNIĘCIA @ 20°C

Pyłosuchy	Przynajmniej 40 minut
Suchy w dotyku	Przynajmniej 2 godziny
Szlifowalny	Przynajmniej 6 godzin
Dostępny	Przynajmniej 12 godzin
Dopasowywanie mebli	Przynajmniej 24 godziny
Układanie dywanów	Przynajmniej 7 dni
Pierwsze czyszczenie na mokro	Przynajmniej 1 miesiąc

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1