

NATURE UO760

sikkens

WOOD COATINGS

INTERIOR

TÉCNOLOGIA

Natural

TIPO DE PRODUCTO

Aceite & Cera

DESCRIPCIÓN DEL PRODUCTO

Aceite translúcido de penetración profunda y fácil de usar. Los colores premezclados se pueden combinar para crear diferentes tonos.

- No humectante
- Buena capacidad de relleno
- Secado rápido



COLOR

Negro / Marrón oscuro / Marrón jengibre / Gris / Marrón claro / Blanco

0.75 L

2.5 L

VIDA ÚTIL

24 meses

CONDICIONES DE ALMACENAJE

Mantener las latas bien cerradas, en un lugar bien ventilado, con temperatura controlada entre 10 y 30°C

CONTENIDO SOLIDO

58.7% ± 1%

DENSIDAD (PESO ESPECÍFICO)

0,93 +/- 1%

VISSCOSIDAD DE ENTREGA

Viscosidad de entrega 20 ± 2 DIN 4 mm (seg.)

PREPARACIÓN DEL SUBSTRATO

	Suelos Mobiliario Superficies de madera en bruto.	P120, P150, P180 P180, P240, P320
	Fuerte o de forma variable madera fuertemente absorbente como abeto, haya, etc.	Primero, pretratar con Nature AND- IO750 incoloro para saturar la madera

TIEMPO DE SECADO @ 20°C

Lijable	Al menos 12 horas
Primero, carga ligera	Al menos 24 horas
Fuerza completa, lista para caminar	Al menos 7 días
Tiempo de exposición con exceso	Al menos 1 horas

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1

INSTRUCCIONES GENERALES

¡Mezclar bien!

Colorante transparente para interiores: Todos los colores se pueden mezclar entre sí. Ajustar la intensidad en cualquier relación de mezcla es posible con el producto N-Nature IO750. El producto debe aplicarse abundantemente, por ejemplo, con brocha, rodillo, esponja, pistola pulverizadora, pistola pulverizadora caliente. (máx. 35°C) Durante el tiempo de exposición de aprox. 60 minutos, las zonas donde el aceite fue absorbido por la madera deben recubrirse inmediatamente para lograr una protección suficiente para evitar manchas. Transcurrido el tiempo de exposición, el exceso debe eliminarse a fondo con una espátula de goma o un paño. Compruebe con antelación si las herramientas son resistentes al aceite y no manchan. madera contra los rayos UV. El producto debe aplicarse abundantemente con brocha o rodillo. Durante el tiempo de exposición de aprox. 30 minutos, las zonas donde el aceite fue absorbido por la madera deben ser repintados inmediatamente para lograr una protección suficiente para evitar manchas. Transcurrido el tiempo de exposición, el exceso de aceite se reparte o se retira mediante un distribuidor hasta obtener un aspecto superficial aceptable y homogéneo. Para aplicaciones exteriores recomendamos aplicar tres manos con secado intermedio durante la noche. Como protección contra la abrasión de los pigmentos (por ejemplo, en el caso de los muebles de jardín), recomendamos aplicar como tratamiento final una capa protectora incolora con N-Nature IO750.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1