

AQUALIT T280

sikkens

WOOD COATINGS

INTERIOR

TECHNOLOGY

Waterborne

PRODUCT TYPE

Topcoat

PRODUCT DESCRIPTION

Lightfast 2K waterborne topcoat with high filling power and very good mechanical and chemical resistance.

- high filling power
- very good mechanical and chemical resistance
- open and closed pores
- non yellowing
- lightfast in all conditions
- Can be applied by roller and brush



COLOUR

Clear

GLOSS LEVEL

10 / 20 / 40

PACK SIZES

AT280-1 - 5 L
AT280-2 - 20 L

SHELF LIFE

12 months

STORAGE CONDITIONS

Keep cans tightly sealed, in a well ventilated place, with controlled temperature between 10 and 30°C

SOLID CONTENT

32% -35% depending on gloss level

DENSITY (SPECIFIC WEIGHT)

1,04 +/- 1%

DELIVER VISCOSITY

40 ± 2 Viscosity at delivery DIN 4 mm (sec.)

PREPARATION OF SUBSTRATES

	Raw wooden surfaces.	Close the pores by repeated application of Aqualit AIS180 or AT280
	Surfaces coated with the pigmented topcoat AQUALIT COLOR	Topcoat must be applied without intermediate sanding after 6 hours up to a maximum of 24 hours.

HARDENER

Hardener	Ratio (by weight)	Pot Life
HWA 6000	20%	Up to 4h

THINNING

tap water

APPLICATION METHOD

Spray application high/low pressure, Roller

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-06-09 / 14




AQUALIT T280

sikkens

WOOD COATINGS

INTERIOR


APPLICATION

			
Spray pressure (bar)	1.5 - 2.0	60 - 90	
Nozzle size (mm)	1.8 - 2.0	0.25-0.28	
Thinner to be added (%)	20	10 - 20	20
Processing viscosity DIN 4mm (sec.)	40	40-50	40
Layer Thickness (g/m ²)	100 - 140	100 - 140	80-120

DRYING TIME @ 20°C

Dust dry	At least 30 minutes
Touch dry	At least 1 hour
Ready for transport	At least 12 hours
Sandable	At least 4 hours

TEST STANDARDS

	DIN 68861/1B Chemical exposure of furniture surfaces
---	--

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-06-09 / 14