

POLYDUR COLOR P390

sikkens

WOOD COATINGS

INTERIOR

TECHNOLOGY

Polyester

PRODUCT TYPE

Primer

PRODUCT DESCRIPTION

High solids solventborne 3K polyester primer with very good hiding power. Suitable for use with high gloss PU topcoats often used on general interior and kitchen furniture.

- styrene-free
- extreme filling power
- no shrinking (ideal as a base coat for high gloss)
- closed pores
- moderate yellowing



COLOUR

White

PACK SIZES

PC-P390-1 - 20 KG

SHELF LIFE

6 months

STORAGE CONDITIONS

Between 15 and 25°C under clean and dry conditions.

SOLID CONTENT

Approx. 71,4 ± 1% in base material

DENSITY (SPECIFIC WEIGHT)

Approx. 1,36 ± 1% kg/l at 20°C

DELIVER VISCOSITY

23 ±2 Viscosity at delivery
DIN 6 mm.

PREPARATION OF SUBSTRATES

	Raw wooden surfaces.	P120, P150, P180
	Exotic wood / woods rich in extractives Wood or MDF in wet rooms	Isolate with QIS160 or SIS130 before.

HARDENER

Hardener	Ratio (by weight)	Pot Life
AUP6571	2%	up to 2 hours when adding 10% of TPU9500-F
HUP6500	2%	

THINNING

TUP9500-F

APPLICATION METHOD

Spray application

APPLICATION

Spray pressure (bar)	1.5 - 3.0
Nozzle size (mm)	2.5-3.0
Thinner to be added (%)	10 - 20
Processing viscosity DIN 4mm (sec.)	16-30 DIN 6mm
Layer Thickness (g/m ²)	150- 250

DRYING TIME @ 20°C

Dust dry	At least 1 hour
Touch dry	At least 90 minutes
Sandable	At least 12 hours
Flash off time after application	20 minutes

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-03-06 / 11

POLYDUR COLOR P390

sikkens

WOOD COATINGS

INTERIOR

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-03-06 / 11