

SolidoColor SC-P310



Product description

Description	Two-pack, solvent-thinnable, white pigmented PU primer based on alkyd.
-------------	--

Range of application

Description	Almost all wooden furniture in the interior. For priming of all common woods and wood-based materials.
-------------	--

Product data

Product code	SC-P310
Packaging size	20 kg
Viscosity at delivery	thixotropic
Solid content in % base material	73.0 ± 1
Solids in % incl. standard hardener	61.7 ± 1
Specific weight in kg/l at 20°C	1.54 ± 1%
Shelf life - Original container unopened	at least 2 years

Preparation of substrates

	Raw wooden surfaces.	P120, P150, P180
	Exotic wood / woods rich in extractives Wood or MDF in wet rooms	Priming with Solido S-IS130

Processing

	Stir thoroughly!
	Mix and apply the product as described under "Hardener Thinner Additives".

Hardener - Thinner - Additives

	Hardening	50% HPU 6210 by weight 80% HPU 6210 by volume
	Dilution	TPU 9201-M (910.33) medium drying
	Pot life 20°C, 65% rel. humidity	up to 6 hours

Application

Spray pressure (bar)	1.5-3.0	110-130
Nozzle size (mm)	2.0-2.5	0.33-0.38
Thinner to be added (%)	10	10
Processing viscosity DIN 4mm (sec.)	21-27	21-27
Coverage per application (g/m ²)	150	150
Coverage (m ² /l)	5	5

Drying time @ 20°C

Dust dry	at least 10 minutes
Touch dry	at least 25 min.
Sandable	at least 4 hours

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-02-17 / 17