

## QuantumColor QC-T470-90-BW01



Product data	
Packaging size	20 kg 5 kg
Viscosity at delivery DIN 4 mm (sec.)	~ 60 depending on the colour
Shelf life – Original container unopened	at least 2 years

Gloss levels		
Product number	Gloss level	DIN 67530 Angle of 60°
QC-T470-90-BW01	high gloss	>90

Preparation of substrates		
	MDF - not affected by moisture MDF - affected by moisture Exotic wood / woods rich in extractives	The recommended coating composition is made with QuantumColor QC-IP350. Final sanding of the primer with grain size P600 - P800.

Processing	
	Stir thoroughly!
	Mix and apply the product as described under "Hardener Thinner Additives". To improve the high gloss effect after a thin coat of the product has been applied and after a flash off time of 30 minutes to two hours, we recommend applying another thin coat. If overpainting is done overnight or at a later time, the entire surface must be slightly sanded with 1200-grit paper and carefully dusted before the next paint coat is applied.

Hardener - Thinner - Additives		
	Hardening	50% of HPU 6300
	Dilution	TPU 9300-F fast drying TPU 9301-S slow drying
	Pot life 20°C, 65% rel. humidity	up to 2 hours

Application		
Spray pressure (bar)	1.5-3.0	110-130
Nozzle size (mm)	1,2 - 1,6	0.18-0.23
Thinner to be added (%)	0-10	0-10
Processing viscosity DIN 4mm (sec.)	15-20	15-20
Coverage per application (g/m²)	80-120	80-120
Coverage (m²/l)	6-9	6-9

Drying time @ 20°C	
Dust dry	at least 30 minutes
Touch dry	at least 4 hours
Ready for transport	at least after 2 days
Sandable	at least 14 hours
Polishable	at least 3 days

Special notes
Decisive for a brilliant high-gloss effect is the careful preparation of the surface and the freedom from dust during application and curing of the high gloss lacquer.
PU lacquers can be applied within one working day without any intermediate sanding. After that period of time, intermediate sanding must be made just before further processing, in order to ensure proper adhesion.
For sufficient opacity and for obtaining the correct colour and for subsequent polishing, the surfaces must be coated with the same product twice. (see Application)
Do not process and dry PU lacquers below 15° C.
PU hardeners are affected by moisture. Always store the hardener in tightly closed original batches.
When using PU hardeners, always follow the safety instructions on the label.
PU hardeners can be stored in the closed original container at a cool and dry place for a maximum of one year.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2020-08-05 / 17