

QuantumColor QC-P330



Product description	
Description	<p>Solventborne, acrylate-based two-pack PU primer with white pigments.</p> <ul style="list-style-type: none"> • Good filling power • Good isolating properties • Smooth surface • Lightfast

Range of application	
Description	<p>Almost all wooden furniture in the interior. For priming of all common woods and wood-based materials. For the coating of MDF in wet-rooms and of wood rich in ingredients, we recommend coating compositions with QuantumColor QC-IP350.</p>

Product data	
Product code	QC-P330
Packaging size	20 kg
Viscosity at delivery DIN 4 mm (sec.)	95 ± 5
Shelf life - Original container unopened	at least 2 years

Preparation of substrates		
	Raw wooden surfaces.	P120, P150, P180
	Exotic wood / woods rich in extractives Wood or MDF in wet rooms	In coating compositions with QuantumColor QC-IP350.

Processing	
	Stir thoroughly!
	Mix and apply the product as described under "Hardener Thinner Additives".

Hardener - Thinner - Additives		
	Hardening	10% of HPU 6300
	Dilution	TPU 9300-F fast drying TPU 9301-S slow drying
	Pot life	up to 8 hours

Application		
Spray pressure (bar)	1.5-3.0	110-130
Nozzle size (mm)	2.0-2.5	0.33-0.38
Thinner to be added (%)	0-20	0-10
Processing viscosity DIN 4mm (sec.)	30-40	40 - 70
Coverage per application (g/m ²)	120-200	120-200
Coverage (m ² /l)	4-7	4-7

Drying time @ 20°C	
Dust dry	at least 20 minutes
Sandable	at least 4 hours

Test standards	
	Hardly inflammable according to the Marine Equipment Directive MED 2014/90/EC.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2022-07-01 / 18