

Nature N-W0780



Product data	
Packaging size	5l 750 ml
Viscosity at delivery DIN 4 mm (sec.)	105 ± 5
Shelf life - Original container unopened	at least 2 years

Preparation of substrates



Floors	P120, P150, P180
Furniture	P180, P240, P320
Raw wooden surfaces.	

Processing



Stir thoroughly!





The product must be applied richly, e.g., by brush, roller, sponge, spray gun, hot spray gun. (max. 45°C) During the exposure time of approx. 60 minutes, sports where the oil was absorbed by the wood must be recoated immediately in order to achieve sufficient protection to prevent spotting. After the exposure time, the excess must be thoroughly removed by means of a rubber squeegee or q wiper. Please test in advance whether the tools are oil-resistant and do not stain. Then, any excess oil is rubbed with a lint-free cotton cloth. Remainders may also be incorporated mechanically by means of a fine abrasive pad. Floors are polished with a fine abrasive pad (white pad) 24 hours after the removal of the excess. By doing so, durability will be considerably increased.

Application	
Coverage (m²/l)	8-15

Special notes

The product is biodegradable; however, it must not be drained into the sewage system. (Regional provisions must

The product can be processed with smooth transition, it is extremely heat resistant (up to 120° C), step proof and dirt resistant.

For wooden surfaces treated with Nature products, it is not possible to indicate

definitive drying times. Terms such as dust dry or sandable in the usual

sense are not relevant.

Test standards



DIN 68861/1C Chemical exposure of furniture surfaces



EN 71-3 Migration of soluble heavy metals



DIN 53160 Part 1 and 2 Resistance to saliva and sweat



Building products complying with the technical DIBT rules. CE marking can be requested for structures likes parquet, stairs, etc. AgBB approval for the use on parquet and wooden floors according to DIN EN



Tox Control - The label for low-emission furniture coatings

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably trough trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2020-07-27 / 14