


RUBBOL® WP 1551-03 5278-729001

sikkens
WOOD COATINGS



Product description	Waterborne, two-pack sprayable primer for wooden components, exterior and interior. - quick drying - good pore wetting - high filling properties - good sanding properties	
Colour	White	
Binder type	Acrylic alkyd resin combination	
Pigments	Titanium dioxide	
Density (specific weight)	approx. 1.26 kg/l	
Packaging	5278-729001-200 - 20 L 5278-729001-820 - 1000 L	
Processing	<p>Spraying wet film thickness: 100 - 150µm. Mixing ratio 100:8 (100 parts of lacquer : 8 parts of hardener) Pot life: approx. 1.5 h after the components have been mixed.</p> <p>Solid content: 36 % by volume; 50 % by weight Solid content including hardener: 41 % by volume; 52 % by weight</p>	
Consumption	100 - 150 ml/m ² , depending on applied wet film thickness per coat without overspray.	
Thinning	Ready to use. If necessary with water max. 5 %.	
Application temperature	15 - 25 °C for substrate, air and material at approx. 60 % relative humidity of air In the case of drying overnight, intermediate sanding is required before the next coat is applied.	
Drying time	Drying at:	Standard atmosphere: 23°C / 50% rel. humidity
		Forced at 40°C
	Dust dry	approx. 2 hours
		approx. 45 minutes
	Sandable	approx. 6 hours
		approx. 2 - 3 hours
	Recoatable	approx. 4 - 8 hours
		approx. 1 - 2 hours
Drying	<p>The drying process of the coating depends on the applied film thickness and may be delayed when using timber with a high extractive contents or drying in damp/cold conditions. During the drying process, always ensure for adequate temperature and ventilation. If the drying conditions are not met, damages within the coating cannot be excluded. For good isolation and water resistance, a drying temperature of 25 - 30 °C is recommend; the temperature should not be less than 20 °C. In case of forced drying at 40 °C and after cooling down, the next coat can be applied after approx. 1 hour. After a minimum drying time of 4 hours up to a maximum of 16 hours, the midcoat can be applied without intermediate sanding. If the following coat is applied at a later time, e.g. after drying overnight, intermediate sanding must be carried out to ensure proper adhesion.</p>	
Cleaning of equipment	Clean with water immediately after use and, if required, add some commercially available washing-up liquid or ST 830.	
Storage	<p>The minimum shelf life in the unopened original container is one year; Storage temperature +5 - +30 ° C. After expiry of the BBD, the product may still be processable, but the product properties may differ from "fresh" material. Therefore, the user must apply material with expired BBD with particular attention. Carefully close containers already opened! Store in a cool but frost-free place. Isocyanate hardeners are moisture-sensitive. Always store in tightly closed containers.</p>	
Disposal	Only empty containers may be recycled. Dispose of material residues according to local regulations. The EC waste code applicable to such material is: 08 01 12	

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our website. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-10-29 / 9

EMEA HQ
Akzo Nobel Hilden GmbH ● Düsseldorf Str. 96 - 100 ● 40721 Hilden ● Germany ● www.akzonobel.com/wood

AN_204450_060919
1/2

AkzoNobel

AN_20450_060919

RUBBOL® WP 1551-03

sikkens
WOOD COATINGS

Safety Data Sheet

Further data in the Material Safety Data Sheet according to 91/155/EEC www.sikkens-wood-coatings.com
Downloads Safety Data Sheets

Warning

Before use, read the identification and product information. Always follow customary protection measures, even when working with low emission products.

VOC Directive

EC limit value for this product (cat. A/d): 150 g/l (2007) / 130 g/l (2010). This product contains max. 30 g/l VOC.

General instructions

The wood moisture content for the application of Sikkens coating systems should be between 12 % and 15 %. The selected wood, the design and the applied layer thicknesses must comply with current technical standards. All horizontal surfaces shall be bevelled by 15 ° and all edges shall be rounded with a radius of at least 2 mm. Joints and open end grains must be sealed to prevent the ingress of water into the structure. The substrates must be dry, free from dust and grease. The selection and application of the coating, especially the colour shade, is important, too. Dark coatings in the exterior may lead to an elevated surface temperature (up to 80 °C).

To ensure correct adhesion of the following coating system, the paint system should not be sanded down to the substrate.

For use in technical industrial companies. Only to be used in approved and recommended Sikkens Wood Coatings coating systems.

Notes

The coating system mentioned here is only an example; other systems are possible. Please refer to the relevant Technical Data Sheets and ask your Sikkens Wood Coatings Sales Representative or the factory for advice about coating systems.

Whenever polyurethane (PUR) material is to be over coated, the surface has to be sanded and sanding dust removed thoroughly just before commencing with further treatment to guarantee perfect bonding.

All external materials coming into contact with the coating system (e.g. putty, adhesive tapes, sealants, cleaners, etc.) must be tested for compatibility by the user.

Coating system

Impregnation	Cetol WP 567 BPD
Primer	Rubbol WP 1551-03
Mid coat	Rubbol WM 270 Rubbol WF 375 Rubbol WF 3300-03-20 , Rubbol WF 3301-03-20 Rubbol WF 3310-03-xx , Rubbol WF 3311-03-xx Rubbol WP 1551-03
Top coat	Rubbol WF 375 Rubbol WF 3300-03-20 , Rubbol WF 3301-03-20 Rubbol WF 3310-03-xx , Rubbol WF 3311-03-xx

Hardening

WH 8500

Hardener

7000-074001 Hardener WH 8500

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-10-29 / 9

EMEA HQ

Akzo Nobel Hilden GmbH ● Düsseldorf Str. 96 - 100 ● 40721 Hilden ● Germany ● www.akzonobel.com/wood

AN_204450_060919

2/2

AkzoNobel

AN_204450_060919