






# Colourit 2K-PUR Lack, koloriert COL-0 COL-7 COL-8 COL-9



Product description		
Description	Two-pack, solvent-thinnable, lightfast PUR varnish with integrated stain. It can be used to modify or match the colour of surfaces already coated with two- pack PUR varnishes. A preview on the surfaces to be modified is possible by means of the available translucent foil fan.	
Range of application		
Description	Almost all wooden furniture in the interior. Open- or closed-pore coatings.	
Product data		
Product code	COL-8 COL-9 COL-0 COL-7	
Packaging size	5l 25l	
Viscosity at delivery DIN 4 mm (sec.)	25 ± 2	
Shelf life – Original container unopened	at least 2 years	
Gloss levels		
Product number	Gloss level	DIN 67530 Angle of 60°
COL-0	matt	10 ± 2
COL-7	gloss	80 ± 2
COL-8	semi gloss	30 ± 2
COL-9	semi matt	15 ± 2
Preparation of substrates		
	Graduated sanding of wood Carefully remove the sanding dust. Coarse-pore wood must be brushed out.	P120, P150, P180
Processing		
	Stir thoroughly!	

Hardener - Thinner - Additives		
	Hardening	10% PUR 5085
	Dilution	S 9004 normal drying S 9029 slow drying
	Pot life 20°C, 65% rel. humidity	up to 24 hours
Application		
Spray pressure (bar)	1.5-2.0	110-130
Nozzle size (mm)	1.6-2.0	0.23-0.28
Thinner to be added (%)	10-20	
Processing viscosity DIN 4mm (sec.)	18-20	25
Coverage per application (g/m²)	90-120	120
Coverage (m²/l)	6-10	7
Drying time @ 20°C		
Dust dry	at least 15 minutes	
Touch dry	at least 45 minutes	
Ready for transport	at least 12 hours	
Sandable	at least 1 hour	
Aftertreatment		
After the indicated drying time we recommend applying a protective varnish coat with Crystallit® in the desired gloss level.		

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2025-03-10 / 34