

AQUA PIGMENT STAIN SNOW FLAKE 6100-769011

AkzoNobel

Type of Product Waterborne Pigmented Stain	Storage Conditions Keep from freezing. Between 15 and 25 °C under clean and dry conditions. Must not be exposed to temperatures below 5°C.
Area of Use Flooring	Methods Sponge roller / Spraying / Dipping / Flowcoat
Additional Information Adhesion and appearance should be evaluated in each specific case. Process line application instructions prevail over the information given in this document.	Application Viscosity Ready for use, delivery viscosity
Packaging 6100-769011-200 - 20 l	Cleaning Water
Notes AQUA PIGMENT STAIN is used where the demand is for a painted, yet transparent look.	Empty Packaging Disposal according to local regulations.
Stains Do not sand the stain. Pigmented stains should be stirred or shaken carefully before use. The stain can be recoated with all types of lacquers. Please note that recoating with waterborne lacquers may cause some bleeding. The stain colour may vary depending on: quantity applied, method of application, type of lacquer used for recoating, variations in the wood substrate, origin of the wood substrate and wood sanding. The stain cannot be used on its own, must always be overcoated.	Additional Drying Information The drying depends on various conditions, i.e. application method, applied amount, time, etc. Ensure good ventilation when drying waterborne products.
Delivery Viscosity Ready for use	HSE Information See Safety Data Sheet for further information.
Density Approx. 1,16 kg/l	
Thinner Water	
Shelf Life 12 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.	

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2021-05-14 / 4

EMEA HQ
 Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood

AkzoNobel