

TECHNOLOGY

Waterborne

PRODUCT TYPE

Filler

PRODUCT DESCRIPTION

A fast drying 1K waterborne parquet joint filler to be mixed with sanding dust.

- Has to be mixed with sanding dust (last intermediate sanding)
- Fast drying
- Easy to use
- Closes joints and holes and reduces side-bonding

**COLOUR**

Clear

PACK SIZES

1 L

SHELF LIFE

12 months

STORAGE CONDITIONS

Keep cans tightly sealed, in a well ventilated place, with controlled temperature between 10 and 30°C

SOLID CONTENT

34.4% ± 1%

DENSITY (SPECIFIC WEIGHT)

1,05 +/- 1%

PREPARATION OF SUBSTRATES

New, untreated floors: Depending on the type of wood and the way of installation, basic sanding must be carried out. Thoroughly remove dirt from the floor by means of vacuuming.	P80 to max. P120
Renovation of already coated wooden floors: First carry out basic sanding to remove the old lacquer film completely. Thoroughly remove dirt from the floor by means of vacuuming.	P80 to max. P120

APPLICATION METHOD

Spatula

GENERAL INSTRUCTION

Carry out intermediate sanding and collect the resulting wood dust in a clean container. Mix Aqualit A-PJF100 and the wood flour in a ratio of 2:1 to 5:1 (depending on the type of wood) in order to make a mixture that can be applied with a spatula. During processing, Aqualit A-PJF100 can be added as thinner. Use a stainless steel spatula to evenly apply the prepared mixture onto the floor and to fill all the small cracks and joints. Apply the product evenly and do not leave any excess on the floor. If cracks and joints become visible during processing, the mixture can be applied again by means of a spatula.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 5