

TECHNOLOGIA

Wodnorozcieńczalny

RODZAJ PRODUKTU

Lakier nawierzchniowy

OPIS PRODUKTU

Światłotrwały wodnorozcieńczalny jednoskładnikowy lakier nawierzchniowy o dobrej przejrzystości i odporności mechanicznej i chemicznej.

- dobra przejrzystość
- dobra odporność mechaniczna i chemiczna
- światłotrwały

**KOLOR**

Bezbarwny

POZIOM POŁYSKU (OK.GU @ 60°)

05 / 20 / 40

20 L

OKRES PRZECHOWYWANIA

12 miesięcy

WARUNKI PRZECHOWYWANIA

Trzymać puszki szczelnie zamknięte, w dobrze wentylowanym pomieszczeniu z kontrolą temperatury pomiędzy 10 a 30°C

ZAWARTOŚĆ CIAŁ STAŁYCH

33% -34.3% w zależności od połysku

GĘSTOŚĆ (CIĘŻAR WŁĄSCIWY)

1.02 - 1.04 +/- 1% w zależności od połysku

LEPKOŚĆ HANDLOWA

120 ± 10 lepkość handlowa DIN 4 mm (s)

PRZYGOTOWANIE SUBSTRATÓW

	Powierzchnie z surowego drewna. Stopniowane szlifowanie drewna. Dokładnie usunąć pył po szlifowaniu. Drewno otwartoporowe należy wyszczotkować.	P120, P150, P180
	Bejcowane powierzchnie drewniane.	Szlifować przed bejcowaniem.
	Powierzchnie z surowego drewna. Drewno egzotyczne / drewno bogate w ekstrakty. Drewno i MDF w pomieszczeniach wilgotnych.	Zaizolować przy użyciu AIS180.
	Powierzchnie pokryte pigmentowanym lakierem nawierzchniowym AQUALIT COLOR	Lakier nawierzchniowy musi być nałożony bez szlifowania międzyoperacyjnego po 6 do maksymalnie 24 godzinach.

ROZCIEŃCZANIE

woda kranowa

METODA APLIKACJI

Aplikacja natryskiem airmix/airless, aplikacja natryskiem wysoko/niskociśnieniowym

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-26 / 2

APLIKACJA

		
Ciśnienie natrysku (bar)	1.5 - 2.0	110 - 130
Rozmiar dyszy (mm)	1.8-2.0	0.25-0.28
Dodatek rozcieńczalnika (%)	5 - 10	5 - 10
Lepkość robocza DIN 4 (s)	40-50	40-50
Grubość warstwy (g/m ²)	100 - 140	100 - 140

CZAS SCHNIĘCIA @ 20°C

Pyłosuchy	Przynajmniej 30 minut
Suchy w dotyku	Przynajmniej 2 godziny
Szlifowalny	Przynajmniej 4 godziny
Gotowy do transportu	Przynajmniej 12 godzin

NORMY TESTOWE

	EN 71-3 Migracja rozpuszczalnych metali ciężkich / DIN 53160 Część 1 i 2 Odporność na ślinę i pot (połyski 05/40 są wyłączone)
--	--

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-26 / 2