

# SOLIDO S122V

**sikkens**

WOOD COATINGS

INTERIOR

## TECHNOLOGY

PU Alkyd


## PRODUCT TYPE

Sealer

## PRODUCT DESCRIPTION

Solventborne 2K sealer with good filling properties specialised for vertical use.

- PU sealer based on alkyd
- Good filling power
- moderate yellowing



## COLOUR

Clear

## PACK SIZES

SS122V - 20 L

## SHELF LIFE

24 months

## STORAGE CONDITIONS

Keep cans tightly sealed, in a well ventilated place, with controlled temperature between 10 and 30°C

## SOLID CONTENT

49.4% ± 1%

## DENSITY (SPECIFIC WEIGHT)

1,01 +/- 1%

## DELIVER VISCOSITY

90 ± 10 Viscosity at delivery DIN 4 mm (sec.)

## PREPARATION OF SUBSTRATES

	Raw wooden surfaces.	P120, P150, P180
	Stained wooden surfaces	Sand prior to staining
	Exotic wood / woods rich in extractives Wood or MDF in wet rooms	Priming with Solido SIS130

## HARDENER

Hardener	Ratio (by weight)
HPU6204	50%

## THINNING

TPU9302-M / TPU9303-S

## APPLICATION METHOD

Spray application airmix/airless, spray application high/low pressure

## APPLICATION

Spray pressure (bar)	1.5 - 2.0	110 - 130
Nozzle size (mm)	1.6 - 2.0	0.23 - 0.28
Thinner to be added (%)	10 - 20	10 - 20
Processing viscosity DIN 4mm (sec.)	18-20	18 - 20
Layer Thickness (g/m <sup>2</sup> )	100 - 150	100 - 150

## DRYING TIME @ 20°C

Dust dry	At least 20 minutes
Touch dry	At least 40 minutes
Sandable	At least 3 hours

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-07-15 / 14