

TECHNOLOGY

PU Alkyd

PRODUCT TYPE

Topcoat

PRODUCT DESCRIPTION

High-gloss, easy-to-polish solventborne 2K topcoat that is ideal for furniture.

- high filling power
- easy to polish
- closed pores
- moderate yellowing



COLOUR

Clear

GLOSS LEVEL

90

PACK SIZES

ST240-1 - 5 L
ST240-2 - 20 L

SHELF LIFE

24 months

STORAGE CONDITIONS

Keep cans tightly sealed, in a well ventilated place, with controlled temperature between 10 and 30°C

SOLID CONTENT

49.7 ± 1%

DENSITY (SPECIFIC WEIGHT)

1.02 ± 1%

DELIVER VISCOSITY

100 ± 10 Viscosity at delivery DIN 4 mm (sec.)

PREPARATION OF SUBSTRATES

	Open-pore coatings	Priming with a suitable sealer of the Solido series.
	Closed-pore coatings	Close the pores by repeated application of a sealer of the Solido series.
	Exotic wood / woods rich in extractives Wood or MDF in wet rooms	Priming with a suitable sealer of the Solido series.

HARDENER

Hardener	Ratio (by weight)	Pot Life	Comment
HPU6207	100%	Up to 10h	higher solids content
HPU6214	100%		Alternative - better non-yellowing properties

THINNING

TPU9202-F
TPU9303-S

APPLICATION METHOD

Spray application airmix/airless, spray application high/low pressure

APPLICATION

		
Spray pressure (bar)	1.5 - 2.0	110 - 130
Nozzle size (mm)	1.6 - 2.0	0.23 - 0.28
Thinner to be added (%)	30	30
Processing viscosity DIN 4mm (sec.)	14 - 16	14 - 16
Layer Thickness (g/m ²)	100-180	100-180

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-03-06 / 19

SOLIDO T240

sikkens

WOOD COATINGS

INTERIOR

DRYING TIME @ 20°C

Dust dry	At least 40 minutes
Touch dry	At least 6 hours
Ready for transport	At least after 2 days
Polishable	After 2 - 3 days

TEST STANDARDS

	DIN 68861/1B Chemical exposure of furniture surfaces
---	--

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-03-06 / 19