

TÉCNOLOGIA

Base Agua

TIPO DE PRODUCTO

Acabado

DESCRIPCIÓN DEL PRODUCTO

Capa de acabado autosellante 1K base agua, transparente y mate.

- buena resistencia a las rayaduras
- buena resistencia a la abrasión



COLOR

Transparente

NIVEL DE BRILLO (APROX. GU @ 60°)

05

5 L
20 L

VIDA ÚTIL

12 meses

CONDICIONES DE ALMACENAJE

Mantener las latas bien cerradas, en un lugar bien ventilado, con temperatura controlada entre 10 y 30°C

CONTENIDO SOLIDO

37.5% ± 1%

DENSIDAD (PESO ESPECÍFICO)

1,05 +/- 1%

VISSCOSIDAD DE ENTREGA

100 ± 10 Viscosidad en la entrega DIN 4 mm (seg.)

PREPARACIÓN DEL SUBSTRATO



La superficie está pretratada con un sellador AQUALIT COLOR

P240,
P280



DILUIR

agua del grifo

MÉTODO DE APLICACIÓN

Aplicación por pulverización airmix/airless, aplicación por pulverización de alta/baja presión

APLICACIÓN

		
Presión de pulverización (bar)	1.5 - 3.0	110 - 130
Tamaño de boquilla (mm)	1.6 - 2.0	0.23 - 0.28
Diluyente a añadir (%)	0-5	0 - 5
Grosor de la Capa (g/m ²)	100 - 130	100 -130

TIEMPO DE SECADO @ 20°C

Seco al polvo	Al menos 30 minutos
Seco al tacto	Al menos 2 horas
Apilable	Al menos 24 horas
Lijable	Al menos 4 horas

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1