

ANTIQUUE EFFECT PATINA

sikkens
WOOD COATINGS
INTERIOR

TECHNOLOGIA

Rozcieńczalnikowy

RODZAJ PRODUKTU

Bejca

OPIS PRODUKTU

Rozpuszczalnikowa patyna jest zawsze nakładana na podkład. Można usunąć nadmiar materiału za pomocą wełny stalowej. Można także dodać do naszej Harmonising Stain Base aby stworzyć różne kolory z harmonizującym drewno efektem.

- Szybkoschnący
- Nieograniczone możliwości tworzenia różnych efektów
- Należy pokryć bezbawnym lakierem rozcieńczalnikowym/wodorozcieńczalnym



KOLOR

Niebieski / Czarny / Szkarłatny Czerwony / Biały / Żółty / Brązowy Żółty / Brązowy / Jasny Żółty / Srebrny / Orzech

1 L
5 L

OKRES PRZECHOWYWANIA

12 miesięcy

WARUNKI PRZECHOWYWANIA

Trzymać puszkę szczelnie zamkniętą, w dobrze wentylowanym pomieszczeniu z kontrolą temperatury pomiędzy 10 a 30°C

ZAWARTOŚĆ CIAŁ STAŁYCH

8-30% ±1 w zależności od koloru

GĘSTOŚĆ (CIĘŻAR WŁAŚCIWY)

0.80 - 1.05 +/- 1% w zależności od koloru

LEPKOŚĆ HANDLOWA

11 ± 1 lepkość handlowa DIN 4 mm (s)

PRZYGOTOWANIE SUBSTRATÓW



Stopniowane szlifowanie drewna. Dokładnie usunąć pył po szlifowaniu. Drewno otwartoporowe należy wyszczotkować.

P120,
P150,
P180

ROZCIEŃCZANIE

TUP9500-F

METODA APLIKACJI

Aplikacja natryskiem

APLIKACJA

Ciśnienie natrysku (bar)	1.0-1.5
Rozmiar dyszy (mm)	0.8-1.3
Dodatek rozcieńczalnika (%)	100-200

CZAS SCHNIĘCIA @ 20°C

Nadaje się do przemalowania	Przynajmniej 10 minut
-----------------------------	-----------------------

OGÓLNA INSTRUKCJA

Te produkty były badane by uzyskać "efekt starzenia". Należy usunąć po 10-20 min. za pomocą wełny stalowej lub Scotch Brite

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-04-28 / 2