

Aqua Positive Stain APB-COLOUR



Product description	
Description	Ready-to-use stain with distinct positive character on coniferous wood. Color-metrics stored. Can also be applied on many type of hardwood.

Range of application	
Description	Almost all types of wood in the interior. Especially on coniferous wood such as spruce, pine, etc. in the interior. Also on softwood with brushed surface for rustic appearance. It is also possible to achieve equalising, excellent colouring on hardwood such as oak or ash without any positive character.

Product data	
Product code	APB-COLOUR
Packaging size	1 l
Viscosity at delivery DIN 4 mm (sec.)	12 sec. ± 2
Shelf life - Original container unopened	at least 1 year

Preparation of substrates		
	Graduated sanding of wood Carefully remove the sanding dust. Coarse-pore wood must be brushed out.	P120, P150, P180
	Optionally wet with water. Sand or smoothen after drying overnight.	

Processing	
	Shake or stir well before use! Always keep the product in motion during the application in order to avoid differences in colour.
	Recommendation - Application with a spray gun. Apply evenly and not too wet. Structured coniferous wood must be sprayed from both sides in the direction of the wood grain.
	Richly apply the product with a staining brush in the direction of the wood grain. Give it some time to absorb, spread diagonally first, then longitudinally. Cross-cut coniferous wood must previously moistened with water in order to avoid spotting.

Brightening/Tinting	
Brightening with product	Brightening with any quantity of Aqua Positive Stain APB/colourless. All stains can be mixed with each other. Nuances can be given with basic colours. Do not use Stain Extract BXF for giving nuances.

Application		
Spray pressure (bar)	1,0 - 1,5	
Nozzle size (mm)	0.8-1.3	
Coverage (m ² /l)	4-6	4-6

Drying time @ 20°C	
Overcoatable	at least 12 hours

Drying time	
Do not accelerate drying by means of heat and/or movement of the air, since this would reduce the development of the positive effect.	

Aftertreatment	
The stain can be coated with a solvent-based or water-based system. To avoid sanding-through at a later time, the surface can be richly coated with Crystallit® Two-Pack PUR Filling and Insulating Primer or Duocryl Two-Pack PUR Filling and Insulating Primer. In order to support the positive character of natural wood, we recommend applying a top coat with a deep-mat varnish such as Crystallit® Two-Pack PUR Deep-Mat Varnish or Variocryl® Deep-Mat Varnish. Priming with Crystallit® Brightening Varnish CL-A or a coat of CL-TM or VC-TM applied twice is also possible. Coating with Naturtrend products is also possible. When doing so, product-related changes in colour must be taken into account.	

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2021-07-02 / 11