

TRÄFF 480 01 WHITE (DURACIDCOLOR-T431-90-B01) 2150-772901

AkzoNobel

Type of Product 2-pack Acid Curing Pigmented Top Coat	Application Conditions Between 20-25 °C for substrate, air and material at approx. 55 % R.H.															
Area of Use Furniture / Interior Joinery	Mixing Ratio Coating : Hardener 10 : 1 (by volume)															
Packaging 2150-772901-120 - 10.8 l	Application Viscosity Conventional spraying: 20-25 sec DIN cup 4 @ 23 °C Curtain coating: 25-35 sec DIN cup 4 @ 23 °C Amount- and choice of thinner depend of application- and line conditions.															
Suitable Primer Träff Tix Primer, Träff Primer, Proff Primer 150	Applied Amount Approx. 110 g/m ² wet film															
Notes Träff 480 is adjusted to Wood Coatings Color System.	Potlife Approx. 24 Hours @ 20 °C															
Binder Alkyd / Amino resins	Cleaning 6500-008001															
Solid Contents Approx. 75 % by weight	Empty Packaging Disposal according to local regulations.															
Delivery Viscosity Approx. 160-170 sec DIN Cup 4 @ 23 °C	Thermal Drying <table border="1"> <thead> <tr> <th>Temperature (°C)</th> <th>20</th> <th>40</th> <th>60</th> <th>80</th> </tr> </thead> <tbody> <tr> <td>Time to (hours)</td> <td></td> <td></td> <td></td> <td></td> </tr> <tr> <td>Stackable.</td> <td>24</td> <td>4</td> <td>1,25</td> <td>0,25-0,50</td> </tr> </tbody> </table>	Temperature (°C)	20	40	60	80	Time to (hours)					Stackable.	24	4	1,25	0,25-0,50
Temperature (°C)	20	40	60	80												
Time to (hours)																
Stackable.	24	4	1,25	0,25-0,50												
Density Approx. 1,25 kg/l	IR Drying <table border="1"> <thead> <tr> <th>IRM</th> <th></th> <th></th> </tr> </thead> <tbody> <tr> <td>Time to (sec)</td> <td></td> <td></td> </tr> <tr> <td>Stackable</td> <td>180</td> <td>240</td> </tr> </tbody> </table>	IRM			Time to (sec)			Stackable	180	240						
IRM																
Time to (sec)																
Stackable	180	240														
Hardener 7200-002001, 7200-003001	Additional Drying Information The drying depends on various conditions, i.e. application method, applied amount, time, etc. Please contact our Technical Staff for specific data concerning curing conditions on your line.															
Thinner 6500-002001, 6500-004001	Gloss Approx. 80-90 GU @ 60°. The final gloss depends on various conditions, i.e. application method, applied amount, drying conditions, etc.															
Shelf Life 24 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.																
Storage Conditions Between 15 and 25 °C under clean and dry conditions.																
Methods Spraying / Curtain coater																

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2021-02-17 / 1

EMEA HQ
 Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood

AkzoNobel

TRÄFF 480 01 WHITE (DURACIDCOLOR-T431-90-B01)



Color
01 WHITE

HSE Information
See Safety Data Sheet for further information.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2021-02-17 / 1

EMEA HQ

Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood

