

## SolidoColor (ICLA 211.09.15/01) SC-T450V-15



| Product data                             |                  |
|--|------------------|
| Packaging size                           | 20 kg            |
| Viscosity at delivery DIN 4 mm (sec.)    | 100 ± 10         |
| Solid content in % base material         | 62.9 ± 1         |
| Solids in % incl. standard hardener      | 50.4 ± 1         |
| Specific weight in kg/l at 20°C          | 1.35 ± 1%        |
| Shelf life - Original container unopened | at least 2 years |

| Gloss levels   |             |                        |
|----------------|-------------|------------------------|
| Product number | Gloss level | DIN 67530 Angle of 60° |
| SC-T450V-15    | semi matt   | 15 ± 2                 |

| Preparation of substrates |  |   |
|---------------------------|--|---|
|                           | Raw wooden surfaces.   | P180, P240, P320  |
|                           | Exotic wood / woods rich in extractives Wood or MDF in wet rooms | In compositions with Solido S- IS130 and a primer of the SolidoColor series. Or in compositions with the isolating primer QuantumColor QC-IP350. Final sanding of the primer with grain size P280 - P320. |
|                           | Wood and wood materials MDF - not affected by moisture           | Pre-treat with a primer of the SolidoColor or QuantumColor series. Final sanding of the primer with grain size P280 - P320.   |

| Processing |  |
|------------|--|
|            | Stir thoroughly!   |
|            | Mix and apply the product as described under "Hardener Thinner Additives". |

| Hardener - Thinner - Additives |                                  |  |
|--------------------------------|----------------------------------|--|
|                                | Hardening                        | 50% HPU 6212 (310.51) by weight                                      |
|                                | Dilution                         | TPU 9302-M (910.17) medium drying<br>TPU 9303-S (910.73) slow drying |
|                                | Pot life 20°C, 65% rel. humidity | up to three hours  |

| Application                         |           |           |
|-------------------------------------|-----------|-----------|
|                                     |           |           |
| Spray pressure (bar)                | 1.5-3.0   | 110-130   |
| Nozzle size (mm)                    | 1.6-2.0   | 0.23-0.28 |
| Thinner to be added (%)             | 10-25     | 10-25     |
| Processing viscosity DIN 4mm (sec.) | 20 - 25   | 20 - 25   |
| Coverage per application (g/m²)     | 100 - 160 | 100 - 160 |
| Coverage (m²/l)                     | 4-7       | 4-7       |

| Drying time @ 20°C  |                     |
|---------------------|---------------------|
| Dust dry            | at least 20 minutes |
| Touch dry           | at least 40 minutes |
| Ready for transport | at least 12 hours   |

| Forced drying                   |            |
|---------------------------------|------------|
| Rest period at room temperature | 10 minutes |
| Hot air drying at 40°C          | 30 minutes |
| Hot air drying at 60°C          | 30 minutes |
| Cooling at room temperature     | 10 minutes |

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2020-08-07 / 5

## SolidoColor (ICLA 211.09.15/01)

### Special notes

Do not process and dry PU lacquers below 15° C.

PU lacquers can be applied within one working day without any intermediate sanding. After that period of time, intermediate sanding must be made just before further processing, in order to ensure proper adhesion.

PU hardeners are affected by moisture. Always store the hardener in tightly closed original batches.

When using PU hardeners, always follow the safety instructions on the label.

PU hardeners can be stored in the closed original container at a cool and dry place for a maximum of one year.

The lacquer base is not lightfast. Depending on the selected colour, slight changes in colour may occur in the course of time. The intensity of yellowing depends on the coat thickness and on the intensity of the ultraviolet radiation of the sunlight. If absolutely non yellowing coatings are desired, please use our products from the QuantumColor series.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2020-08-07 / 5

**EMEA HQ**  
Akzo Nobel Hilden GmbH ● Düsseldorf Str. 96 - 100 ● 40721 Hilden ● Germany ● [www.akzonobel.com/wood](http://www.akzonobel.com/wood)

AN\_204450\_060919