

Product description			Drying time		
Solventborne opaque 2-pack topcoat for wooden constructions, exterior and interior. - good weather resistance - high surface hardness			Drying at:	Standard atmosphere: 23°C / 50% rel. humidity	Forced at 40°C
Colour			Dust dry	approx. 2 - 4 hours	approx. 1 - 2 hours
Colours from RAL, Sikkens 5051 Color Concept and NCS NCS S0502-Y			Sandable	approx. 4 - 5 hours	approx. 2 - 3 hours
Gloss levels			Recoatible	approx. 4 - 5 hours	approx. 2 - 3 hours
Product name		Gloss	Stackable	approx. 8 hours	approx. 3 - 4 hours
	B00	Matt	Drying		
RUBBOL® SF 332	B01	Matt	The drying process of the coating depends on the applied film thickness and may be delayed when using timber with a high extractive contents or drying in damp/cold conditions. During the drying process, always ensure for adequate temperature and ventilation. If the drying conditions are not met, damages within the coating cannot be excluded. For good crosslinking, temperature should not be lower than 18°C.		
	NCS-S0502-Y	Matt			
Binder type			Cleaning of equipment		
Alkyd			With Thinner ST 820 (6500-020001) or turpentine.		
Pigments			Storage		
Titanium dioxide			The minimum shelf life (BBD) in the unopened original container is one year; Storage temperature +5 - +30 ° C. After expiry of the BBD, the product may still be processable, but the product properties may differ from "fresh" material. For that reason, the user must apply expired material with particular attention. Started containers must be closed carefully! Store in a cool but frost-free place. PU hardeners are sensitive to moisture. Please, store the hardener always in tightly closed containers.		
Processing			Disposal		
Spraying Wet film thickness: approx. 120 µm Mixing ratio 10 : 3 (10 parts of lacquer; 3 parts of hardener) Processing viscosity is approx. 20 - 40 seconds in DIN cup 4 mm with a material temperature of 20 °C. Pot life: approx. 4 h after the components have been mixed			Only empty containers may be recycled. Dispose of material residues according to local regulations. The EC waste code applicable to such material is: 08 01 11		
Consumption			Safety Data Sheet		
approx. 120 ml/m2, depending on applied wet film thickness per coat without overspray.			Further data in the Material Safety Data Sheet according to 91/155/EEC www.sikkens-wood-coatings.com Downloads Safety Data Sheets		
Thinning					
Adjust to processing viscosity with max. 20% of Thinner ST 820 (6500-020001), if required.					
Application temperature					
15 - 25 °C for substrate, air and material at approx. 60 % relative humidity of air In the case of drying overnight, intermediate sanding is required before the next coat is applied.					

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-09-22 / 28

EMEA HQ
Akzo Nobel Hilden GmbH ● Düsseldorf Str. 96 - 100 ● 40721 Hilden ● Germany ● www.akzonobel.com/wood

AN_204450_060919
1/2

AkzoNobel

AN_20450_060919

RUBBOL® SF 332

sikkens
WOOD COATINGS

Warning

Before use, read the identification and product information. Always follow customary protection measures, even when working with low emission products.

VOC Directive

EC limit value for this product (cat. A/j): 550g/l (2007)/500 g/l (2010). This product contains max. 450 g/l VOC.

General instructions

The wood moisture content for the application of Sikkens coating systems should be between 12 % and 15 %. The selected wood, the design and the applied layer thicknesses must comply with current technical standards. All horizontal surfaces shall be bevelled by 15 ° and all edges shall be rounded with a radius of at least 2 mm. Joints and open end grains must be sealed to prevent the ingress of water into the structure. The substrates must be dry, free from dust and grease. The selection and application of the coating, especially the colour shade, is important, too. Dark coatings in the exterior may lead to an elevated surface temperature (up to 80 °C).

To ensure correct adhesion of the following coating system, the paint system should not be sanded down to the substrate.

For use in technical industrial companies. Only to be used in approved and recommended Sikkens Wood Coatings coating systems.

Notes

The coating system mentioned here is only an example; other systems are possible. Please refer to the relevant Technical Data Sheets and ask your Sikkens Wood Coatings Sales Representative or the factory for advice about coating systems.

Whenever polyurethane (PUR) material is to be over coated, the surface has to be sanded and sanding dust removed thoroughly just before commencing with further treatment to guarantee perfect bonding.

All external materials coming into contact with the coating system (e.g. putty, adhesive tapes, sealants, cleaners, etc.) must be tested for compatibility by the user.

Coating system

Impregnation	Cetol WP 567 BPD
Primer	Rubbol SP 142 / SP 144
Top coat	Rubbol SF 332

Hardening

7000-012009 Hardener SH 820

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-09-22 / 28

EMEA HQ

Akzo Nobel Hilden GmbH ● Düsseldorf Str. 96 - 100 ● 40721 Hilden ● Germany ● www.akzonobel.com/wood

AN_204450_060919

2/2

AkzoNobel

AN_20450_060919