# DURACID COLOR P360

# SIKKENS

INTERIOR

# TÉCNOLOGIA

Curado ácido

#### **TIPO DE PRODUCTO**

Primer

# **DESCRIPCIÓN DEL PRODUCTO**

Imprimación base disolvente 2K, sin formaldehído, de secado rápido y con buena capacidad de relleno.

- secado rápido
- buena capacidad de relleno
- sin formaldehído



### COLOR

Blanco

20 KG

# **VIDA ÚTIL**

12 meses en el envase original sin abrir

#### **CONDICIONES DE ALMACENAJE**

Entre 15 y 25°C en condiciones limpias y secas.

#### **CONTENIDO SOLIDO**

Aprox. 65 % en peso

# **DENSIDAD (PESO ESPECÍFICO)**

Aprox. 1,29 kg/l

# **VISSCOSIDAD DE ENTREGA**

Aprox. 140-160 seG DIN COPA 4 @ 23 °C

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably trough trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1

Akzo Nobel Hilden GmbH, Düsseldorfer Str. 96 - 100, 40721 Hilden, Germany. www.sikkens-wood-coatings.com

#### **TEMPERATURA DE APLICACIÓN**

Entre 20-25  $^{\circ}\mathrm{C}$  para sustrato, aire y material a aprox. 55 % H.R.

#### **ENDURECEDOR (EN PESO)**

5 Días @ 20 °C

### DILUIR

TAC9400-M; TAC9402-S

#### MÉTODO DE APLICACIÓN

Aplicación con pistola airmix/airless, aplicación con pistola de alta/baja presión, cortina

#### **APLICACIÓN**

		Ē	
Viscosidad de aplicación DIN 4 mm (seg.)	25-30 seg DIN copa @ 23°C	30-50 seg DIN copa 4 @ 23 °C	25-40 seg DIN copa 4 @ 23 °C
Grosor de la Capa (g/m²)	120	120	120

# TIEMPO DE SECADO @ 20°C

Lijable	Al menos 1 horas
Apilable	Al menos 4 horas

