




Naturtrend Holzdesign-Öl

NHDO-10-NATURAL-WHITE NHDO-11-STONE-GREY NHDO-20-TEAK NHDO-30-MAHOGANY NHDO-60-WALNUT NHDO-70-BASALT-BLACK



| Product description | | Processing | |
|---|--|--|--|
| Description | Pigmented, deeply penetrating, solvent-containing oil for coloured design. |  | Stir thoroughly! |
| Range of application | | Application | |
| Description | Almost all wooden furniture in the interior. The use on floors and stairs is possible but not recommended, since depending on the strain "pathways" might appear and the surface might require renovation more rapidly. Even exotic wood and woods rich in extractives can be coated without any special preparation. For exterior applications on not dimensionally stable components like floors, garden furniture, summer houses, fences and balcony panelling. | Coverage (m²/l) opaque (without removing the excess) | 6-8 |
| | | Coverage (m²/l) transparent (with removal of excess) | 8-15 |
| Product data | | Drying time @ 20°C | |
| Product code | NHDO-30-MAHOGANY | Sandable | at least 12 hours |
| | NHDO-11-STONE-GREY | First, light load | at least 24 hours |
| | NHDO-60-WALNUT | Full strength, ready to walk on | at least 7 days |
| | NHDO-70-BASALT-BLACK | Exposure time with rich excess | 60 minutes |
| | NHDO-10-NATURAL-WHITE | | |
| Product color | 10 Natural white | | |
| Packaging size | 2.5 l 750 ml | | |
| Viscosity at delivery DIN 4 mm (sec.) | 20 ± 2 | | |
| Shelf life – Original container unopened | at least 2 years | | |
| Gloss levels | | Aftertreatment | |
| Product number | NHDO-10-NATURAL-WHITE | After drying and previous sanding (furniture P320/P400, floors P240), the product can be applied again. We recommend applying a top coat of Naturtrend Project Oil NPO in order to protect the pigments. Naturtrend surfaces must be given a follow-up treatment from time to time. Appropriate products can be found in the Cleaning & Care section . In case wear should be too heavy, complete rebuild might be useful. | |
| | NHDO-20-TEAK | Special notes | |
| | NHDO-30-MAHOGANY | Tools should be cleaned with Naturtrend Furniture Cleanser NMR, Special Intensive Cleanser IR or white spirit. | |
| | NHDO-60-WALNUT | Test standards | |
| | NHDO-70-BASALT-BLACK |  | DIN 68861/1C Chemical exposure of furniture surfaces |
| Preparation of substrates | | | |
|  | Raw wooden surfaces. Furniture | P180, P240, P320 | |

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2025-03-10 / 34