

QUANTUM COLOR T4850

sikkens

WOOD COATINGS

INTERIOR

TECHNOLOGY

PU Acrylic

PRODUCT TYPE

Topcoat

PRODUCT DESCRIPTION

2k Solvent-based, semi-matt, lightfast, very well-filling pigmented topcoat system. Colour mixing system for the creation of almost any colour according to Sikkens, RAL, NCS, etc. or to your own sample.

- Outstanding coverage even after a single coat
- High sag resistance
- Easy to paint on vertical surfaces
- Maximum ring and scratch resistance
- Maximum hardness
- Good sealing and filling properties on raw MDF (even in damp rooms)
- Can be used on suitable surfaces without filler



COLOUR

WHITE / BLACK / BLUE / BORDO / YELLOW / YELLOW ORANGE / GREEN / OCKER / OXIDE RED / RED / RAL 9010 / RAL 9016

GLOSS LEVEL

20% hardener: 20 ± 2
10% hardener: 13 ± 2

SHELF LIFE

24 months in original, unopened package

STORAGE CONDITIONS

Keep cans tightly sealed, in a well ventilated place, with controlled temperature between 10 and 30°C

SOLID CONTENT

approx 45% ±5% depending on colour

DENSITY (SPECIFIC WEIGHT)

approx 1,10 ±0,10 kg/l depending on colour

DELIVER VISCOSITY

90 ± 6 sec. DIN 4

PREPARATION OF SUBSTRATES

	Raw wooden surfaces.	P180, P240, P320
	Exotic wood / woods rich in extractives	Coat with Quantum Color IP350
	MDF - not affected by moisture	Apply Quantum Color P340 until a closed, even surface is obtained. Final sanding of primer with grain size P280 - P320.
	MDF - affected by moisture	Apply Quantum Color IP350 until a closed, even surface is obtained. Final sanding of the primer with grain size P280 - P320.

HARDENER

Hardener	Ratio (by weight)	Pot Life
HPU6300	10%	Up to 8h
HPU6300	20%	Up to 4h

THINNING

TPU 9300-F, Fast drying
TPU 9301-S, Slow drying

APPLICATION METHOD

Stir thoroughly!
Mix and apply the product as described under "Hardener" and "Thinning"

Pot life 20°C, 65% rel. humidity:
10% hardener: up to 8h
20% hardener: up to 4h

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-04-17 / 30

APPLICATION

		
Spray pressure (bar)	1.5 - 3.0	90 - 120
Nozzle size (mm)	1.6 - 2.0	0.23 - 0.28
Thinner to be added (%)	10 - 30	0 - 10
Processing viscosity DIN 4mm (sec.)	30 - 40	40 - 60
Layer Thickness (g/m ²)	120 - 200	150 - 200

DRYING TIME @ 20°C

Dust dry	10% hardener: at least 15 minutes 20% hardener: at least 25 minutes
Touch dry	10% hardener: at least 45 minutes 20% hardener: at least 60 minutes
Sandable	10% hardener: at least 2 hours 20% hardener: at least 2 hours
Ready for transport	10% hardener: at least 12 hours 20% hardener: at least 16 hours

GENERAL INSTRUCTION

Aftertreatment

After sanding with P280-320, the surface can be reworked at any time with the same product. With a mixing ratio of 10:1, reworking with PUR paints is possible within a maximum of one working day (8 hours). After this time, intermediate sanding is necessary shortly before further processing to ensure a perfect bond. With a mixing ratio of 5:1, the reworking time is max. 4 hours. After this time, intermediate sanding is also necessary here to ensure intermediate adhesion. With a mixing ratio of 10:1, finishing with a lightfast clear coat system, e.g. Quantum 260-xx is recommended. With a mixing ratio of 5:1, finishing with a clear coat is not necessary.

Special notes

After a minimum drying time of 14 days, surfaces mixed with 20% hardener obtain a robust, easy-to-clean anti-graffiti surface. Do not process and dry PU lacquers below 15° C. PU hardeners are affected by moisture. Always store the hardener in tightly closed original batches. When using PU hardeners, always follow the safety instructions on the label. PU hardeners can be stored in the closed original container at a cool and dry place for a maximum of one year.

Maximum application quantity for MED
2014/90/EU per application (g/m²): 120µm

TEST STANDARDS

	DIN 68861/1B Chemical exposure of furniture surfaces
---	--

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-04-17 / 30