SOFTFEEL CLEAR B00
2525-008031

AkzoNobel

Type of Product
2-pack Polyurethane Lacquer

Area of Use
Interior Joinery

Packaging
2525-008031-120 - 10 L

Notes
Soft feel B00, 2525-008031 is a two-pack polyurethane Clear coat which gives a leather-like surface on the coated object. Soft feel is intended for top coating of interior parts, for example within the automotive industry. The product can in certain cases be used directly on plastic. Soft feel B00 could be used as a Clear coat but is also a mixing base adapted for mixing with the Tintex Colorants. The product fulfils hydrolyse testing according to Volvo. Soft feel is not recommended on table surfaces.

Remarks
The hardener is an isocyanate.

Binder
Polyester

Solid Contents
47 +/- 2 % by weight
Approx. 40 % by volume

VOC
This product contains max. 554 g/l VOC.

Delivery Viscosity
85 +/- 10 sec DIN Cup 4 @ 23 °C

Density
1,02 +/- 0,02 kg/l

Hardener
7000-005009 or 7000-009001

Thinner
6500-008001 (62119), approx. 10 vol. % by use of Hardener 7000-009001./ 6500-011001 (62140) by use of Hardener 7000-005009./ 6500-008001 (62119) is used when applied on plastic with hardener 7000-005009.

Shelf Life
12 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.

Storage Conditions
Between 15 and 25 °C under clean and dry conditions.

Methods
Airless spraying / Low pressure spraying / Curtain coater

Application Conditions
Between 20-25 °C for substrate, air and material at approx. 55 % R.H.

Mixing Ratio
Coating:Hardener 2525-008031 – 6 parts:7000-005009 – 1 part by volume
Coating:Hardener 2525-008031 – 5 parts:7000-009001 – 1 part by volume

Application Viscosity
25-27 sec DIN cup 4 @ 23 °C mixed with hardener.

Applied Amount
30-40 µm wet film

Potlife
Approx. 1 Hours @ 20 °C

Cleaning
6500-008001

Empty Packaging
Disposal according to local regulations.

Thermal Drying
Flash off: 5-10 min. forced air @ 20 °C.
Drying: 30 min. forced air @ 80 °C.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably trough trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-11-06 / 8

EMEA HQ
Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood

AkzoNobel

AN_20450_060919

Gloss

Approx. 2,5 +/- 0,5% GU @ 60°.
The final gloss depends on various conditions, i.e. application method, applied amount, drying conditions, etc.

Color

Clear

HSE Information

See Safety Data Sheet for further information.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably trough trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2026-11-06 / 8

EMEA HQ
Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood

AN_20450_060919