

**SOFTFEEL CLEAR  
B00  
2525-008031**

**AkzoNobel**

<b>Type of Product</b> 2-pack Polyurethane Lacquer	<b>Thinner</b> 6500-008001 (62119), approx. 10 vol. % by use of Hardener 7000-009001./ 6500-011001 (62140) by use of Hardener 7000-005009./ 6500-008001 (62119) is used when applied on plastic with hardener 7000-005009.
<b>Area of Use</b> Interior Joinery	<b>Shelf Life</b> 12 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.
<b>Packaging</b> 2525-008031-120 - 10 l	<b>Storage Conditions</b> Between 15 and 25 °C under clean and dry conditions.
<b>Notes</b> Soft feel B00, 2525-008031 is a two-pack polyurethane Clear coat which gives a leather-like surface on the coated object. Soft feel is intended for top coating of interior parts, for example within the automotive industry. The product can in certain cases be used directly on plastic. Soft feel B00 could be used as a Clear coat but is also a mixing base adapted for mixing with the Tintex Colorants. The product fulfils hydrolyse testing according to Volvo. Soft feel is not recommended on table surfaces.	<b>Methods</b> Airless spraying / Low pressure spraying / Curtain coater
<b>Remarks 1</b> The hardener is an isocyanate.	<b>Application Conditions</b> Between 20-25 °C for substrate, air and material at approx. 55 % R.H.
<b>Binder</b> Acrylic resin	<b>Mixing Ratio</b> Coating:Hardener 2525-008031 - 6 parts:7000-005009 - 1 part by volume Coating:Hardener 2525-008031 - 5 parts:7000-009001 - 1 part by volume
<b>Solid Contents</b> 47 +/- 2 % by weight Approx. 40 % by volume	<b>Application Viscosity</b> 25-27 sec DIN cup 4 @ 23 °C mixed with hardener.
<b>VOC</b> This product contains max. 554 g/l VOC.	<b>Applied Amount</b> 30-40 µm wet film
<b>Delivery Viscosity</b> 85 +/- 10 sec DIN Cup 4 @ 23 °C	<b>Potlife</b> Approx. 1 Hours @ 20 °C
<b>Density</b> 1,02 +/- 0,02 kg/l	<b>Cleaning</b> 6500-008001
<b>Hardener</b> 7000-005009 or 7000-009001	<b>Empty Packaging</b> Disposal according to local regulations.
	<b>Thermal Drying</b> Flash off: 5-10 min. forced air @ 20 °C. Drying: 30 min. forced air @ 80 °C.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2021-03-15 / 3

**EMEA HQ**  
Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood

**AkzoNobel**

# SOFTFEEL CLEAR B00

## Gloss

Approx. 2,5 +/- 0,5% GU @ 60°.  
The final gloss depends on various conditions, i.e. application method, applied amount, drying conditions, etc.

## Color

Clear

## HSE Information

See Safety Data Sheet for further information.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2021-03-15 / 3

### EMEA HQ

Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 [www.akzonobel.com/wood](http://www.akzonobel.com/wood)