

# TI911 SB65 BLUE 8200-150001

# AkzoNobel

<b>Type of Product</b> Pigment Paste	<b>Remarks</b> Mixing instructions: the TI911 colorants – colour formulation is added into a small volume of base, directly in the delivery can. Shake the can well for at least 2-3 min., then add to the can, the remaining amount of clear base to achieve final volume.
<b>Packaging</b> 8200-150001-010 - 1 L	
<b>Notes</b> TI911 is a light fast, acid aniline stain conc. for use in dilution with selected thinners for application on wood, indoors. Can only be used in WB stains. Suitable for tinting in some WB lacquer, (max. add. 5 w/w%) and intermixable to any shade. Please contact our Technical Staff.	<b>HSE Information</b> See Safety Data Sheet for further information.
<b>Stains</b> The stain cannot be used on its own, must always be overcoated. Do not sand the stain. Pigmented stains should be stirred or shaken carefully before use.	
<b>Solid Contents</b> Approx. 20 % by weight	
<b>Density</b> Approx. 1,12 kg/l	
<b>Thinner</b> Type of thinner is depending on application method. Please consult our Technical Staff.	
<b>Shelf Life</b> 12 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.	
<b>Storage Conditions</b> Between 15 and 25 °C under clean and dry conditions. Keep from freezing. Must not be exposed to temperatures below 5°C.	
<b>Remarks</b> When producing WB-stain, mix TI911 with 6000-003011 or similar WB base. The final product is named TINTEX STAIN WST 911.	
<b>Empty Packaging</b> Disposal according to local regulations.	

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2022-07-07 / 3

EMEA HQ  
Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood

# AkzoNobel