

TEHNOLOGIJA

Waterborne

TIP IZDELKA

Nadlak

OPIS IZDELKA

Low VOC waterborne 1K topcoat with great blocking resistance and chemical resistance, as well as excellent levelling and smoothing properties.

- great blocking resistance
- great levelling and smoothness
- Optimised for vertical and airmix application
- low VOC (<63g/l)



BARVA

Base Neutral BN00/Base White BW01

STOPNJA SIJAJA (PRIBL. GU PRI 60°)

20

ROK UPORABE

12 mesecev v originalni, neodprti embalaži

VSEBNOST TRDNIH SNOVI

BW01: Approx. 46 % by weight
BN00: Approx. 37 % by weight

GOSTOTA (SPECIFIČNA TEŽA)

BW01: Approx. 1,16 kg/l
BN00: Approx. 1,03 kg/l

DOBAVNA VISKOZNOST

Approx. 1900-2100 mPas Brookfield RV # 4/50 @ 23°C

HOS (G/L)

EU limit value for this product (cat. A/d): 130 g/l (2010). This product contains max. 63 g/l

PRIPRAVA PODLAG

MDF - brez vpliva zaradi vlage	Predhodno obdelajte s temeljnim premazom AQUALIT COLOR. Končno brušenje temeljnega premaza z zrnatostjo P280-P320.
--------------------------------	--



REDČENJE

voda iz pipe

NAČIN NANOSA

Nanos z brizganjem z zrakom/brezračno, nanos z brizganjem pod visokim/nizkim tlakom

NANOS

		
Tlak brizganja (bar)	1.5 - 3.0	110 - 130
Velikost šobe (mm)	1.8 - 2.0	0.23 - 0.28
Razredčilo za dodajanje (%)	5 - 10	
Debelina sloja (g/m ²)	100 - 120	100 - 120

ČAS SUŠENJA PRI 20°C

Prašno suho	Vsaj 45 minut
Suho na dotik	After 1,5 - 2 hours
Možnost brušenja	Vsaj 4 ur
Nanos več slojev	Vsaj 12 ur

AQUALIT COLOR T4450

sikkens

WOOD COATINGS

INTERIOR**SPLOŠNA NAVODILA**

For vertical Airmix application, a 0.23mm nozzle is recommended.

For vertical cup spray gun application, a 2.0mm nozzle and dilution with max. 5% water is recommended. For horizontal surfaces, dilution of up to max. 10% is possible.

AkzoNobel