

TECHNOLOGIA

PU Akrylowy

RODZAJ PRODUKTU

Lakier nawierzchniowy

OPIS PRODUKTU

Rozcieńczalnikowy jednoskładnikowy bezbarwny lakier nawierzchniowy nadający naturalny wygląd drewnu dębu. Światłotrwały bezbarwny akrylowy lakier nawierzchniowy. Produkt daje głęboki mat naturalnego drewna bez podkreślania usłojenia. Drewno jest chronione, ale wygląda na surowe.

- Naturalny wygląd
- Światłotrwały
- Nieżółknący/ul}

**KOLOR**

Bezbarwny

POZIOM POŁYSKU (OK.GU @ 60°)

05

5 L
20 L**OKRES PRZECHOWYWANIA**

24 miesięcy w oryginalnym, nieotwieranym opakowaniu

WARUNKI PRZECHOWYWANIA

Przechowywać pojemniki szczelnie zamknięte, w dobrze wentylowanym pomieszczeniu, z kontrolowaną temperaturą w zakresie od 10 do 30°C

ZAWARTOŚĆ CIAŁ STAŁYCH

5.4% ± 1%

GĘSTOŚĆ (CIĘŻAR WŁAŚCIWY)

0,88 +/- 1%

LEPKOŚĆ HANDLOWA18 ± 2 lepkość
handlowa DIN 4 mm (s)**PRZYGOTOWANIE SUBSTRATÓW**

Powierzchnie z surowego drewna. Stopniowane szlifowanie drewna. Dokładnie usunąć pył po szlifowaniu. Drewno otwartoporowe należy wyszczotkować.

P120,
P150,
P180**METODA APLIKACJI**

Aplikacja natryskiem airmix/airless, aplikacja natryskiem wysoko/niskociśnieniowym

APLIKACJA

Ciśnienie natrysku (bar)	1.5 - 2.0	110 - 130
Rozmiar dyszy (mm)	1.6 - 2.0	0.23 - 0.28
Lepkość robocza DIN 4 (s)	16-20	16-20
Grubość warstwy (g/m²)	100 - 120	100 - 120

CZAS SCHNIĘCIA @ 20°C

Pyłosuchy	Przynajmniej 20 minut
Suchy w dotyku	Przynajmniej 40 minut
Szlifowalny	Przynajmniej 1 godzina
Gotowy do transportu	Przynajmniej 12 godzin

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-03-20 / 3