

# QUANTUM COLOR P330

**sikkens**

WOOD COATINGS

INTERIOR

## TÉCNOLOGÍA

PU Acrílico

## TIPO DE PRODUCTO

Primer

## DESCRIPCIÓN DEL PRODUCTO

Imprimación 2K, PU acrílico, base disolvente, multifuncional para un acabado muy brillante. Su buena capacidad de relleno produce una superficie lisa que no amarillea y ofrece una alta resistencia a los impactos.

- buena capacidad de relleno
- superficie lisa adecuada para un alto brillo
- resistente a la luz
- alta resistencia a los impactos
- buenas propiedades aislantes



## COLOR

Blanco

5 KG  
20 KG

## VIDA ÚTIL

24 meses

## CONDICIONES DE ALMACENAJE

Mantener las latas bien cerradas, en un lugar bien ventilado, con temperatura controlada entre 10 y 30°C

## CONTENIDO SOLIDO

55,2% ± 1%

## DENSIDAD (PESO ESPECÍFICO)

1,35 +/- 1%

## VISSCOSIDAD DE ENTREGA

65 sec. ± 2 DIN 6mm

## PREPARACIÓN DEL SUBSTRATO



Superficies de madera en bruto. P120, P150, P180

## ENDURECEDOR (EN PESO)

HPU6300	10%	hasta 8h
---------	-----	----------

## DILUIR

TPU 9300-F, Secado rápido  
TPU 9301-S, Secado lento

## MÉTODO DE APLICACIÓN

Aplicación por pulverización airmix/airless, aplicación por pulverización de alta/baja presión

## APLICACIÓN

Presión de pulverización (bar)	1.5 - 3.0	110 - 130
Tamaño de boquilla (mm)	2.0 - 2.5	0.33 - 0.38
Diluyente a añadir (%)	0-20	0 - 10
Viscosidad de aplicación DIN 4 mm (seg.)	30-40	40 - 70
Grosor de la Capa (g/m²)	120 - 200	120 - 200

## TIEMPO DE SECADO @ 20°C

Seco al polvo	Al menos 20 minutos
Lijable	Al menos 4 horas

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-27 / 2

# QUANTUM COLOR P330

**sikkens**

WOOD COATINGS

INTERIOR

## ESTÁNDARES DE PRUEBA



Tox Control - La etiqueta para muebles de bajas emisiones revestimientos

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-27 / 2