

AQUALIT COLOR P341

sikkens

WOOD COATINGS

INTERIOR

TECHNOLOGIE

Wasserlöslich

PRODUKTART

Grundierung

PRODUKTBESCHREIBUNG

Die Mischbasis des 1K Füllers auf Wasserbasis neutral (BN00) wird dazu verwendet, einen Füller im Wunschfarbton herzustellen, um eine bessere Deckkraft zu erzielen.



FARBTON

Basis transparent Bn00

18.4 KG

HALTBARKEIT

12 Monate

LAGERBEDINGUNGEN

Zwischen 15 und 25 ° C unter sauberen und trockenen Bedingungen.

FESTKÖRPER

53,9% ± 1

DICHTE

1,30 +/- 1%

VORBEHANDLUNG UNTERGRÜNDE



Rohe Holzflächen. Abgestufter Holzschliff. Schleifstaub sorgfältig entfernen. Grobporige Hölzer ausbürsten.

P120,
P150,
P180

VERDÜNNUNG

Leitungswasser

APPLIKATIONSVERFAHREN

Lackierapplikation Airmix/Airless, Lackierapplikation Hoch-, Niederdruck

APPLIKATION

		
Spritzdruck (bar)	1.5 - 3.0	110 - 130
Düsengröße (mm)	2.0 - 2.5	0.33 - 0.38
Verdünner-Zugabe (%)	0 - 10	0 - 5
Verarbeitungsviskosität DIN 4mm (sec.)	100-140	120-140
Schichtdicke (g/m ²)	100 - 120	100 - 120

TROCKENZEIT BEI 20°C.

Schleifbar	ab 2 Stunden
Stapelbar	ab 2 Stunden

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1