






Unocryl 1K-Wasser Parkettlack

UC-P-8 UC-P-9



Product description		
Description	Water-thinnable, colourless one-pack parquet varnish for high mechanical demands.	
Range of application		
Description	The product is suitable for all usual types of wood parquet and cork. Also suitable to renovate floors and stairs.	
Product data		
Product code	UC-P-8 UC-P-9	
Packaging size	1 l 5l	
Viscosity at delivery DIN 4 mm (sec.)	20 ± 2	
VOC Directive EC limit value for this product (cat. A/i): 140 g/l (2010)	This product contains max. 90 g/l VOC.	
Shelf life - Original container unopened	at least 1 year	
Gloss levels		
Product number	Gloss level	DIN 67530 Angle of 60°
UC-P-8	semi gloss	45 ± 2
UC-P-9	semi matt	20 ± 2
Preparation of substrates		
	Unocryl One-Pack Parquet Sealer must be applied and sanded in accordance with the Technical Data Sheet.	P120, P150
Processing		
	Stir thoroughly!	
Hardener - Thinner - Additives		
	Dilution	not required if necessary tap water
Application		
Processing viscosity DIN 4mm (sec.)	20	
Coverage per application (g/m ²)	70-125	
Coverage (m ² /l)	8-15	
Drying time @ 20°C		
Dust dry	at least 40 minutes	
Touch dry	at least 90 min.	
Sandable	at least 4 hours	
Accessible	at least 12 hours	
Fitting of furniture	at least 24 hours	
Laying of carpets	at least 7 days	
First wet cleaning	at least 1 month	
Aftertreatment		
After sufficient drying, sand with a disk sander and P 150 sanding disks. Apply Unocryl One-Pack Parquet Varnish UC-P 8, 9 again. For sufficient protection, a total of three coats of lacquer is required.		
Test standards		
	Abrasion resistance according to DIN 68861, Part 2	
	Slip resistance according to DIN 51130 and ASR A1.5 / 1.2 with the addition of 3% Structure Powder fine STP-F.	

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2022-05-02 / 5