

AQUAFLEX COLORANT AN114

8000-603009

AkzoNobel

Type of Product
Tinter for Waterborne products
Additional Information
AQUA FLEX COLORANT is used for all types of W/B paints within Wood Coatings Color System. 14 universal tinting pastes are available in the system. Maximum adding of Aqua Flex Colorant is 200 impulses per 0,9 ltr. paint or 13,5 vol%.
Packaging
8000-603009-011 - 1 L
Pigment Concentrates
The colorant contains only one pigment which is chosen with great care to comply with all relevant demands to the final product (heat resistance, outdoor durability, etc.). Never shake the tinter. Always stir the tinters by hand before filling the machine. In order to avoid drying of the paste, the nozzle seal must be used on the Tintex dispenser.
Density
Approx. 1,09 kg/l
Shelf Life
24 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.
Storage Conditions
Keep from freezing. Between 15 and 25 °C under clean and dry conditions.
Remarks
Can be stored for 3 months in opened packing.
Empty Packaging
Disposal according to local regulations.
Color
Black strong, Pigment Index P.BL.7
HSE Information
See Safety Data Sheet for further information.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-07-15 / 7

EMEA HQ

Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood

AkzoNobel