

Type of Product Waterborne Pigmented Top Coat	Shelf Life 12 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.																
Area of Use Furniture / Interior Joinery	Storage Conditions Between 15 and 25 °C under clean and dry conditions. Keep from freezing. Must not be exposed to temperatures below 5°C.																
Packaging 3225-010151-200 - 20 L	Methods Spraying																
Suitable Primer UV Primer, Aqua Surf	Application Conditions Between 20-25 °C for substrate, air and material at approx. 55 % R.H.																
Notes AQUALITCOLOR AC-T470 is very fast drying with good stacking properties and early surface hardness. The quality is adjusted to Wood Coatings Color System for waterborne industrial products, (tinting with AquaFlex Colorants).	Application Viscosity Conventional spraying: 25-60 sec DIN cup 4 @ 23 °C Airless spraying: 35-60 sec DIN cup 4 @ 23 °C																
Waterborne Products NOTE: Continuous stirring of the product is not recommended. Great risk that the physical properties may change negatively with increase in viscosity and deterioration of the anti foaming ability. If larger packaging such as containers are used contact our technical staff for advice.	Applied Amount Approx. 100 g/m ² wet film																
Binder Acrylic	Cleaning 8500-070001. Rinse with water after cleaning.																
Solid Contents Approx. 31 % by weight	Empty Packaging Disposal according to local regulations.																
Delivery Viscosity Approx. 130-140 sec DIN Cup 4 @ 23 °C The viscosity of this product is determined using controlled laboratory conditions, methods and instruments. Any measurements made under other conditions may lead to different results.	Thermal Drying <table border="1"> <thead> <tr> <th>Temperature (°C)</th> <th>20</th> <th>40</th> <th>60</th> </tr> </thead> <tbody> <tr> <td>Time to (min)</td> <td></td> <td></td> <td></td> </tr> <tr> <td>Sandable</td> <td>120</td> <td>45</td> <td>15</td> </tr> <tr> <td>Stackable.</td> <td>180</td> <td>60</td> <td>20</td> </tr> </tbody> </table>	Temperature (°C)	20	40	60	Time to (min)				Sandable	120	45	15	Stackable.	180	60	20
Temperature (°C)	20	40	60														
Time to (min)																	
Sandable	120	45	15														
Stackable.	180	60	20														
Density Approx. 1,05 kg/l	IR Drying <table border="1"> <tbody> <tr> <td>IRM</td> <td></td> </tr> <tr> <td>Time to (sec)</td> <td></td> </tr> <tr> <td>Sandable</td> <td>120-150</td> </tr> </tbody> </table>	IRM		Time to (sec)		Sandable	120-150										
IRM																	
Time to (sec)																	
Sandable	120-150																
Thinner Water																	

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-06-28 / 3

Additional Drying Information

Ensure good ventilation when drying waterborne products. The drying depends on various conditions, i.e. application method, applied amount, time, etc. Please contact our Technical Staff for specific data concerning curing conditions on your line.

Gloss

Approx. 15 GU @ 60°. The final gloss depends on various conditions, i.e. application method, applied amount, drying conditions, etc.

HSE Information

See Safety Data Sheet for further information.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-06-28 / 3

EMEA HQ

Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood