

# SANDOSEAL 199 (AQUALIT A S-150)

## 3000-007001

# AkzoNobel

<b>Type of Product</b> Waterborne Transparent Sealer	<b>Methods</b> Spraying															
<b>Area of Use</b> Furniture / Interior Joinery	<b>Application Viscosity</b> Ready for use, delivery viscosity															
<b>Packaging</b> 3000-007001-200 - 20 L 3000-007001-201 - 20 L 3000-007001-820 - 1000 L	<b>Applied Amount</b> Approx. 1x120 g/m <sup>2</sup> wet film															
<b>Notes</b> SANDOSEAL 199 (AQUALIT A S-150) is used as sealer in a waterborne system. Combinations with solventborne finishes have to be tested and approved. Gives very good sanding- and filling properties and good transparency on most types of wood.	<b>Cleaning</b> 8500-070001. Rinse with water after cleaning.															
<b>Binder</b> Acrylic	<b>Empty Packaging</b> Disposal according to local regulations.															
<b>Solid Contents</b> Approx. 33 % by weight	<b>Remarks</b> <b>Thickener:</b> Please consult our Technical Staff. <b>Tinting:</b> Waterborne Stain Colorants or Pigment Pastes.															
<b>Delivery Viscosity</b> Approx. 800-1000 mPas Brookfield RV # 3/5 @ 23 °C	<b>Thermal Drying</b> <table border="1"> <thead> <tr> <th>Temperature (°C)</th> <th>20</th> <th>40</th> </tr> </thead> <tbody> <tr> <td>Time to (min)</td> <td></td> <td></td> </tr> <tr> <td>Touch dry</td> <td>30</td> <td>10</td> </tr> <tr> <td>Sandable</td> <td>45</td> <td>15</td> </tr> <tr> <td>Stackable.</td> <td>90</td> <td>30</td> </tr> </tbody> </table>	Temperature (°C)	20	40	Time to (min)			Touch dry	30	10	Sandable	45	15	Stackable.	90	30
Temperature (°C)	20	40														
Time to (min)																
Touch dry	30	10														
Sandable	45	15														
Stackable.	90	30														
<b>Density</b> Approx. 1,02 kg/l	<b>Additional Drying Information</b> Before stacking the objects, cooling is required to ensure that the surface temperature measured in stack does not exceed 30°C. Ensure good ventilation when drying waterborne products. Please contact our Technical Staff for specific data concerning curing conditions on your line.															
<b>pH value</b> Approx. 7,7 - 8,2	<b>HSE Information</b> See Safety Data Sheet for further information.															
<b>Thinner</b> Water																
<b>Shelf Life</b> 24 months in original, unopened package when stored following the storage conditions mentioned below. After the expiry date, contact our Technical Staff for an estimation of usability.																
<b>Storage Conditions</b> Between 15 and 25 °C under clean and dry conditions. Keep from freezing.																

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability. AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2024-01-31 / 6

EMEA HQ  
 Akzo Nobel Industrial Coatings AB SE-205 17 Malmö Tel. +46 40 35 50 00 Fax +46 40 35 51 32 www.akzonobel.com/wood

# AkzoNobel