

TECHNOLOGIA

Wodnorozcieńczalny

RODZAJ PRODUKTU

Podkład

OPIS PRODUKTU

Mocno wypełniający wodnorozcieńczalny biały podkład, który może być używany jako jedno- lub dwuskładnikowy. Jeśli używany jest w układzie dwuskładnikowym, może być stosowany w pomieszczeniach mokrych dzięki doskonałym właściwościom izolującym. Dodatkowo, jako dwuskładnikowy, może być wykonany rozcieńczalnikowymi produktami z serii Quantum i Solido.

- mocno wypełniający, szczególnie na krawędziach MDF
- może być używany jako jedno lub dwuskładnikowy (dwuskładnikowy zapewnia doskonałą izolację przed barwiącymi składnikami drewna i pozwala na użytkowanie w mokrych pomieszczeniach)
- jako dwuskładnikowy jest preparatem poprawiającym przyczepność do wielu plastików i metali
- świątłotrwały



KOLOR

Biały

5 KG
20 KG

OKRES PRZECHOWYWANIA

12 miesięcy

WARUNKI PRZECHOWYWANIA

Trzymać puszki szczelnie zamknięte, w dobrze wentylowanym pomieszczeniu z kontrolą temperatury pomiędzy 10 a 30°C

ZAWARTOŚĆ CIAŁ STAŁYCH

54.9% ± 1%

GĘSTOŚĆ (CIĘŻAR WŁAŚCIWY)

1,40 +/- 1%

LEPKOŚĆ HANDLOWA

140 ± 5

PRZYGOTOWANIE SUBSTRATÓW

	Powierzchnie z surowego drewna. Stopniowane szlifowanie drewna. Dokładnie usunąć pył po szlifowaniu. Drewno otwartoporowe należy wyszczotkować.	P120, P150, P180
	Płyty ofoliowane (np. HPL lub melamina) muszą być starannie wyszlifowane. Płyty pokryte folią podkładową muszą być czyste i wolne od smarów i silikonu.	P320 / P400
	Metale należy odfłuścić czystym rozcieńczalnikiem takim jak TPU 9300-F i lekko przeszlifować drobnym papierem ściernym. Plastik należy oczyścić i przeszlifować włókniną lub gąbką szlifierską. Jako promotor adhezji, produkt należy nanosić wyłącznie z utwardzaczem jako dwuskładnikowy. Nanoszący powinien sprawdzić adhezję.	P400, P600

TEMPERATURA APLIKACJI

Pomiędzy 20-25 °C dla substratu, powietrza i materiału przy ok. 55% W.W.

UTWARDZACZ (WAGOWO)

HWA 6000	10% wagowo / 15% objętościowo	do 4 godzin	Utwardzanie opcjonalne
----------	-------------------------------	-------------	------------------------

ROZCIEŃCZANIE

woda kranowa

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1

METODA APLIKACJI

Aplikacja natryskiem airmix/airless, aplikacja natryskiem wysoko/niskociśnieniowym

APLIKACJA

		
Ciśnienie natrysku (bar)	1.5 - 3.0	110 - 130
Rozmiar dyszy (mm)	2.0 - 2.5	0.33 - 0.38
Dodatek rozcieńczalnika (%)	Jednoskładnikowy: 0-5% Dwuskładnikowy: 5-10%	5 - 10
Lepkość robocza DIN 4 (s)	100-140	120-140
Grubość warstwy (g/m ²)	120-300	120-300

CZAS SCHNIĘCIA @ 20°C

Pyłosuchy	Przynajmniej 30 minut
Suchy w dotyku	Przynajmniej 2 godziny
Szlifowalny	Przynajmniej 6 godzin

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2023-01-09 / 1