

QUANTUM COLOR RESIDUES PRIMER

sikkens

WOOD COATINGS

INTERIOR

TECHNOLOGY

PU Acrylic

PRODUCT TYPE

Filler

PRODUCT DESCRIPTION

Transforms solvent-based two-pack PUR residues of Sikkens® paints into a high-build two-pack PUR filler. Can also be used to produce a two-pack PU primer in a certain colour shade.

For almost all wooden furniture in the interior. For priming of all common woods and wood-based materials. For the coating of MDF in wet rooms and of wood rich in ingredients, we recommend coating compositions with our product Quantum Color IP350.



PACK SIZES

5261317 - 10 KG

SHELF LIFE

24 months in original, unopened package

STORAGE CONDITIONS

Keep cans tightly sealed, in a well ventilated place, with controlled temperature between 10 and 30°C

SOLID CONTENT

76,5% ± 3%

DENSITY (SPECIFIC WEIGHT)

1,66 ± 0,02

DELIVER VISCOSITY

Pasty

PREPARATION OF SUBSTRATES

	Raw wooden surfaces. Graduated sanding of wood. Carefully remove the sanding dust. Coarse-pore wood must be brushed out	P120, P150, P180
	Wood or MDF in wet rooms	Prime with Quantum Color IP350.

HARDENER

Hardener	Ratio (by volume) @ 23°C	Pot Life
HPU6300	12%	Up to 4h @20°C

THINNING

TPU9300-F normal drying
TPU9301-S slow drying

APPLICATION METHOD

Stir thoroughly!
Mix and apply the product as follows:

Unhardened residues of Sikkens Interior two-pack PUR paints/varnishes can be collected in the pre-filled original container of Residues Primer up to the upper mark.

Products suitable: all Quantum fillers, all Quantum paints, opaque and translucent, even metallic paints and high-gloss paints and all mixtures of these products.

Thoroughly stir when the upper filling mark is reached. The mixture can then be hardened and applied.

Fill the pre-filled original container of Residues Primer with a Quantum Color top coat in the colour of your choice up to the upper filling mark or take the desired quantity of Residues Primer and mix it 1:1 with a Quantum Color top coat and stir thoroughly. The finished mixture must then be hardened and applied.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2025-12-15 / 10

QUANTUM COLOR RESIDUES PRIMER

sikkens

WOOD COATINGS

INTERIOR

APPLICATION

		
Spray pressure (bar)	1.5 - 3.0	110 - 130
Nozzle size (mm)	2.0 - 2.5	0.33 - 0.38
Thinner to be added (%)	As required	As required
Processing viscosity DIN 4mm (sec.)	Varies depending on the mixture	Varies depending on the mixture
Layer Thickness (g/m ²)	120 - 200	120 - 200

DRYING TIME @ 20°C

Dust dry	At least 30 minutes
Touch dry	At least 2 hours
Sandable	At least 6 hours

GENERAL INSTRUCTION

Aftertreatment:

After sanding with P280-320 grit paper, the surface can be retreated with the same product at any time. After the desired filling result has been obtained, further coating can be made with the Sikkens Interior systems Aqualit Color or Quantum Color after the surface has been slightly sanded.

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed - in writing - the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2025-12-15 / 10