

AQUALIT T2700

sikkens
WOOD COATINGS
INTERIOR

TECHNOLOGY

Waterborne

PRODUCT TYPE

Topcoat

PRODUCT DESCRIPTION

A fast drying Waterborne 1K self-sealing clear topcoat with excellent clarity. Very good antisagging properties, suitable for both horizontal and vertical application. Good hardness and easy to sand. Very good scratch resistance and good pore filling properties making this great choice for general furniture.

- Very good scratch resistance
- Very good stacking
- Easy to use and apply (Suitable for vertical and horizontal application)
- Open and closed pores
- Good mechanical and chemical resistance



COLOUR

Clear

GLOSS LEVEL

05 / 10 / 20 / 30

PACK SIZES

AT2700 - 20 L

SHELF LIFE

12 months in original, unopened package

STORAGE CONDITIONS

Between 15 and 25°C under clean and dry conditions.

SOLID CONTENT

30,80%

DENSITY (SPECIFIC WEIGHT)

1,07 ± 1%

VOC (G/L)

44g/l

PREPARATION OF SUBSTRATES

P120, P150, P180

APPLICATION TEMPERATURE

+10 - 30 °C for substrate, air and material at approx. 60 % R.H.

THINNING

tap water

APPLICATION METHOD

Spray application airmix/airless, spray application high/low pressure

APPLICATION

| Spray pressure (bar) | 1.5 - 3.0 | 80 - 100 |
|-------------------------------------|-----------|-----------|
| Nozzle size (mm) | 1.8 - 2.0 | 0,25-0.33 |
| Thinner to be added (%) | 0 - 10 | 0 - 10 |
| Layer Thickness (g/m ²) | 100 - 130 | 100 -130 |

DRYING TIME @ 20°C

| | |
|-----------|---------------------|
| Dust dry | At least 45 minutes |
| Sandable | At least 3 hours |
| Stackable | At least 16 hours |

Products from AkzoNobel Wood Coatings are exclusively produced for professional and industrial users, who have a basic knowledge of the handling and application of chemical/technical products for surface design. The processing instructions for reaching the qualities given in the leaflets should be regarded as non-binding recommendations and do not constitute any warranty. These recommendations are based on our experiences, including test series, and should facilitate and promote the work of our clients. Any potential deviation from ideal working conditions is within the responsibility of our clients and may affect the (end) result of the application. The purchaser is not relieved from his duties to inspect the product and its suitability for the surface to be processed, preferably through trial processing. If in any doubt as to the handling or processing of the purchased product, our material experts as well as our application and laboratory technicians will help you to the best of their ability.

AkzoNobel, of course, guarantees an impeccable quality of its products in its product specifications, yet the use thereof lies entirely within the responsibility of the purchaser. As long as we have not guaranteed – in writing – the specific characteristics and suitability of a product for a contractually agreed purpose, any advice or information given regarding the application or handling, even if the advice or information is given to the best of our knowledge, will not be binding nor will it constitute a warranty. AkzoNobel's liability for the use of its products by its customers is limited in its

General Sales and Delivery Conditions, to which the purchaser is hereby referred. The applicable version of the Technical Data Sheet for this product can be downloaded from our websites. Previous versions of the Technical Data Sheets are rendered void with the issue of a new one. Date of issue: 2025-08-20 / 20